



WEAR	NORMAL
CONTAMINATION	NORMAL
FLUID CONDITION	NORMAL

Machine Id
8111798
Component
Diesel Engine
Fluid
VALVOLINE 15W40 (--- GAL)

RECOMMENDATION

Resample at the next service interval to monitor. Please specify the component make and model with your next sample.

Test	UOM	Method	Limit/Abn	Current	History1	History2
Sample Number		Client Info		IL0034277	IL05802182	IL05644075
Sample Date		Client Info		20 Dec 2023	14 Mar 2023	06 Sep 2022
Machine Age	mls	Client Info		167048	75230	62141
Oil Age	mls	Client Info		0	0	0
Filter Age	mls	Client Info		0	0	0
Oil Changed		Client Info		Changed	N/A	N/A
Filter Changed		Client Info		Changed	N/A	N/A
Sample Status				NORMAL	NORMAL	NORMAL

WEAR

All component wear rates are normal.

Iron	ppm	ASTM D5185m	>100	35	21	34
Chromium	ppm	ASTM D5185m	>20	2	2	3
Nickel	ppm	ASTM D5185m	>4	<1	0	0
Titanium	ppm	ASTM D5185m		<1	<1	<1
Silver	ppm	ASTM D5185m	>3	0	0	<1
Aluminum	ppm	ASTM D5185m	>20	6	6	8
Lead	ppm	ASTM D5185m	>40	9	5	12
Copper	ppm	ASTM D5185m	>330	1	1	2
Tin	ppm	ASTM D5185m	>15	3	1	2
Vanadium	ppm	ASTM D5185m		<1	<1	0
White Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE

CONTAMINATION







There is no indication of any contamination in the oil.

Silicon	ppm	ASTM D5185m	>25	8	7	8
Potassium	ppm	ASTM D5185m	>20	12	11	16
Fuel		WC Method	>5	<1.0	<1.0	<1.0
Water		WC Method	>0.2	NEG	NEG	NEG
Glycol		WC Method		NEG	NEG	NEG
Soot %	%	*ASTM D7844	>3	0.6	0.4	0.6
Nitration	Abs/cm	*ASTM D7624	>20	11.1	11.1	14.6
Sulfation	Abs/.1mm	*ASTM D7415	>30	26.1	23.6	27.3
Silt	scalar	*Visual	NONE	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.2	NEG	NEG	NEG

FLUID CONDITION

The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

Sodium	ppm	ASTM D5185m		2	3	1
Boron	ppm	ASTM D5185m	39	35	61	4
Barium	ppm	ASTM D5185m	1	0	2	<1
Molybdenum	ppm	ASTM D5185m	49	78	68	61
Manganese	ppm	ASTM D5185m	1	<1	<1	1
Magnesium	ppm	ASTM D5185m	616	663	615	732
Calcium	ppm	ASTM D5185m	1554	1465	1248	1194
Phosphorus	ppm	ASTM D5185m	899	939	769	648
Zinc	ppm	ASTM D5185m	1069	1197	962	858
Sulfur	ppm	ASTM D5185m	2624	2991	2596	2276
Oxidation	Abs/.1mm	*ASTM D7414	>25	23.5	21.4	27.6
Base Number (BN)	mg KOH/g	ASTM D2896	6.9	4.2	5.8	5.6
Visc @ 100°C	cSt	ASTM D445	13.6	12.5	12.6	13.2



Certificate L2367

Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513
Sample No. : IL0034277 **Received** : 12 Jan 2024
Lab Number : 06058957 **Diagnosed** : 12 Jan 2024
Unique Number : 10830339 **Diagnostician** : Wes Davis
Test Package : FLEET

To discuss this sample report, contact Customer Service at 1-800-237-1369.

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

TAMPA IDEALEASE
 5951 ORIENT ROAD
 TAMPA, FL
 US 33610-9565
 Contact: Russ Cook
 russcook@idealease.com
 T: (813)626-9285
 F: (844)270-1356