



OIL ANALYSIS REPORT

WEAR	NORMAL
CONTAMINATION	SEVERE
FLUID CONDITION	ABNORMAL

Machine Id
673
Component
Diesel Engine
Fluid
DIESEL ENGINE OIL SAE 15W40 (17 QTS)

RECOMMENDATION

We advise that you check the fuel injection system. We recommend that you drain the oil from the component if this has not already been done. We recommend an early resample to monitor this condition.

Test	UOM	Method	Limit/Abn	Current	History1	History2
Sample Number		Client Info		WC0870839	WC0792913	WC0706495
Sample Date		Client Info		08 Dec 2023	22 Mar 2023	13 Jun 2022
Machine Age	mls	Client Info		248727	244300	234208
Oil Age	mls	Client Info		0	0	0
Filter Age	mls	Client Info		0	0	0
Oil Changed		Client Info		Not Changd	Not Changd	Not Changd
Filter Changed		Client Info		Not Changd	Not Changd	Not Changd
Sample Status				SEVERE	NORMAL	NORMAL

WEAR

All component wear rates are normal.

Iron	ppm	ASTM D5185m	>130	12	10	17
Chromium	ppm	ASTM D5185m	>10	1	0	<1
Nickel	ppm	ASTM D5185m	>4	<1	0	0
Titanium	ppm	ASTM D5185m	>2	<1	0	0
Silver	ppm	ASTM D5185m	>2	0	0	0
Aluminum	ppm	ASTM D5185m	>20	3	3	5
Lead	ppm	ASTM D5185m	>20	0	0	2
Copper	ppm	ASTM D5185m	>125	9	0	1
Tin	ppm	ASTM D5185m	>4	<1	0	<1
Vanadium	ppm	ASTM D5185m		0	0	<1
White Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE

CONTAMINATION












There is a high amount of fuel present in the oil. Tests confirm the presence of fuel in the oil.

Silicon	ppm	ASTM D5185m	>25	12	3	5
Potassium	ppm	ASTM D5185m	>20	9	0	4
Fuel	%	ASTM D3524	>3.0	8.6	<1.0	<1.0
Water		WC Method	>0.2	NEG	NEG	NEG
Glycol		WC Method		NEG	NEG	NEG
Soot %	%	*ASTM D7844	>6	0.1	0.8	1.2
Nitration	Abs/cm	*ASTM D7624	>20	5.4	10.0	12.7
Sulfation	Abs/.1mm	*ASTM D7415	>30	20.4	19.7	24.3
Silt	scalar	*Visual	NONE	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.2	NEG	NEG	NEG

FLUID CONDITION

The BN result indicates that there is suitable alkalinity remaining in the oil. Fuel is present in the oil and is lowering the viscosity. The oil is no longer serviceable due to the presence of contaminants.

Sodium	ppm	ASTM D5185m	>158	14	3	5
Boron	ppm	ASTM D5185m	250	54	38	24
Barium	ppm	ASTM D5185m	10	6	0	0
Molybdenum	ppm	ASTM D5185m	100	38	83	81
Manganese	ppm	ASTM D5185m		2	<1	<1
Magnesium	ppm	ASTM D5185m	450	392	68	29
Calcium	ppm	ASTM D5185m	3000	1398	2186	1945
Phosphorus	ppm	ASTM D5185m	1150	705	981	886
Zinc	ppm	ASTM D5185m	1350	801	1276	1081
Sulfur	ppm	ASTM D5185m	4250	2358	4051	3222
Oxidation	Abs/.1mm	*ASTM D7414	>25	18.1	14.6	18.3
Base Number (BN)	mg KOH/g	ASTM D2896	8.5	10.0	6.8	7.3
Visc @ 100°C	cSt	ASTM D445	14.4	10.2	13.8	14.7



Certificate L2367

Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513
Sample No. : WC0870839 **Received** : 12 Jan 2024
Lab Number : 06059830 **Diagnosed** : 16 Jan 2024
Unique Number : 10831212 **Diagnostician** : Wes Davis
Test Package : MOB 1 (Additional Tests: FuelDilution, PercentFuel, TBN)

WAKE COUNTY PUBLIC SCHOOL SYSTEM
 1551 ROCK QUARRY ROAD
 RALEIGH, NC
 US 27610
 Contact: DEVIN WEBER
 dweber@wcpss.net
 T: (919)856-8076
 F: x:

To discuss this sample report, contact Customer Service at 1-800-237-1369.
 * - Denotes test methods that are outside of the ISO 17025 scope of accreditation.
 Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)