



OIL ANALYSIS REPORT

WEAR	NORMAL
CONTAMINATION	NORMAL
FLUID CONDITION	NORMAL

Machine Id
1774
Component
Diesel Engine
Fluid
DIESEL ENGINE OIL SAE 15W40 (--- QTS)

RECOMMENDATION

Resample at the next service interval to monitor. Please specify the component make and model with your next sample.

Test	UOM	Method	Limit/Abn	Current	History1	History2
Sample Number		Client Info		WC0870705	WC0743110	WC0671043
Sample Date		Client Info		03 Jan 2024	20 Sep 2022	16 Feb 2022
Machine Age	mls	Client Info		54000	24383	10803
Oil Age	mls	Client Info		0	0	0
Filter Age	mls	Client Info		0	0	0
Oil Changed		Client Info		Not Changd	Not Changd	Not Changd
Filter Changed		Client Info		Not Changd	Not Changd	Not Changd
Sample Status				NORMAL	NORMAL	ABNORMAL

WEAR

Metal levels are typical for a new component breaking in.

Iron	ppm	ASTM D5185m	>100	7	11	85
Chromium	ppm	ASTM D5185m	>20	<1	<1	2
Nickel	ppm	ASTM D5185m	>4	<1	0	0
Titanium	ppm	ASTM D5185m		0	0	0
Silver	ppm	ASTM D5185m	>3	0	0	0
Aluminum	ppm	ASTM D5185m	>20	7	22	▲ 28
Lead	ppm	ASTM D5185m	>40	0	0	0
Copper	ppm	ASTM D5185m	>330	<1	4	234
Tin	ppm	ASTM D5185m	>15	<1	0	<1
Vanadium	ppm	ASTM D5185m		0	0	0
White Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE

CONTAMINATION











There is no indication of any contamination in the oil.

Silicon	ppm	ASTM D5185m	>25	5	8	▲ 32
Potassium	ppm	ASTM D5185m	>20	10	49	▲ 106
Fuel		WC Method	>5	<1.0	<1.0	<1.0
Water		WC Method	>0.2	NEG	NEG	NEG
Glycol		WC Method		NEG	NEG	NEG
Soot %	%	*ASTM D7844	>3	0.3	0.3	0.7
Nitration	Abs/cm	*ASTM D7624	>20	9.3	9.5	12.9
Sulfation	Abs/.1mm	*ASTM D7415	>30	18.5	19.7	25.2
Silt	scalar	*Visual	NONE	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.2	NEG	NEG	NEG

FLUID CONDITION

The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

Sodium	ppm	ASTM D5185m	>158	2	2	3
Boron	ppm	ASTM D5185m	250	41	40	32
Barium	ppm	ASTM D5185m	10	4	2	0
Molybdenum	ppm	ASTM D5185m	100	82	78	45
Manganese	ppm	ASTM D5185m		0	<1	4
Magnesium	ppm	ASTM D5185m	450	103	54	622
Calcium	ppm	ASTM D5185m	3000	1896	2101	1092
Phosphorus	ppm	ASTM D5185m	1150	949	990	603
Zinc	ppm	ASTM D5185m	1350	1130	1190	761
Sulfur	ppm	ASTM D5185m	4250	3631	4204	978
Oxidation	Abs/.1mm	*ASTM D7414	>25	14.6	14.4	27.4
Base Number (BN)	mg KOH/g	ASTM D2896	8.5	6.4	7.9	6.7
Visc @ 100°C	cSt	ASTM D445	14.4	13.1	13.8	13.0



Certificate L2367

Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513
Sample No. : WC0870705 **Received** : 12 Jan 2024
Lab Number : 06059836 **Diagnosed** : 15 Jan 2024
Unique Number : 10831218 **Diagnostician** : Wes Davis
Test Package : MOB 1 (Additional Tests: TBN)

WAKE COUNTY PUBLIC SCHOOL SYSTEM
 1551 ROCK QUARRY ROAD
 RALEIGH, NC
 US 27610
 Contact: DEVIN WEBER
 dweber@wcpss.net
 T: (919)856-8076
 F: x:

To discuss this sample report, contact Customer Service at 1-800-237-1369.

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)