



OIL ANALYSIS REPORT

WEAR	NORMAL
CONTAMINATION	NORMAL
FLUID CONDITION	NORMAL

Machine Id
FSP141548
 Component
Diesel Engine
 Fluid
DIESEL ENGINE OIL SAE 15W40 (--- QTS)

RECOMMENDATION

Resample at the next service interval to monitor. Please specify the component make and model with your next sample. Please specify the brand, type, and viscosity of the oil on your next sample.

Test	UOM	Method	Limit/Abn	Current	History1	History2
Sample Number		Client Info		WC0891651	WC0861065	WC0722763
Sample Date		Client Info		09 Jan 2024	10 Oct 2023	01 Dec 2022
Machine Age	mls	Client Info		0	145046	113974
Oil Age	mls	Client Info		0	0	10000
Filter Age	mls	Client Info		0	0	10000
Oil Changed		Client Info		Changed	Changed	Changed
Filter Changed		Client Info		Changed	Changed	Changed
Sample Status				NORMAL	ATTENTION	NORMAL

WEAR

All component wear rates are normal.

Iron	ppm	ASTM D5185m	>100	14	37	17
Chromium	ppm	ASTM D5185m	>20	<1	1	0
Nickel	ppm	ASTM D5185m	>4	0	<1	0
Titanium	ppm	ASTM D5185m		0	<1	0
Silver	ppm	ASTM D5185m	>3	0	0	0
Aluminum	ppm	ASTM D5185m	>20	2	9	4
Lead	ppm	ASTM D5185m	>40	3	▲ 25	6
Copper	ppm	ASTM D5185m	>330	4	7	2
Tin	ppm	ASTM D5185m	>15	<1	2	<1
Vanadium	ppm	ASTM D5185m		0	0	0
White Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE

CONTAMINATION







There is no indication of any contamination in the oil.

Silicon	ppm	ASTM D5185m	>25	5	8	7
Potassium	ppm	ASTM D5185m	>20	3	8	4
Fuel		WC Method	>5	<1.0	<1.0	<1.0
Water		WC Method	>0.2	NEG	NEG	NEG
Glycol		WC Method		NEG	NEG	NEG
Soot %	%	*ASTM D7844	>3	1	2.6	1.3
Nitration	Abs/cm	*ASTM D7624	>20	9.5	16.7	12.4
Sulfation	Abs/.1mm	*ASTM D7415	>30	21.1	29.4	24.0
Silt	scalar	*Visual	NONE	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.2	NEG	NEG	NEG

FLUID CONDITION

The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

Sodium	ppm	ASTM D5185m	>158	0	6	0
Boron	ppm	ASTM D5185m	250	<1	2	1
Barium	ppm	ASTM D5185m	10	0	1	0
Molybdenum	ppm	ASTM D5185m	100	67	71	66
Manganese	ppm	ASTM D5185m		0	2	<1
Magnesium	ppm	ASTM D5185m	450	1089	1049	936
Calcium	ppm	ASTM D5185m	3000	1205	1219	1127
Phosphorus	ppm	ASTM D5185m	1150	1142	1017	1061
Zinc	ppm	ASTM D5185m	1350	1341	1317	1241
Sulfur	ppm	ASTM D5185m	4250	3821	3550	3612
Oxidation	Abs/.1mm	*ASTM D7414	>25	17.3	25.1	20.4
Base Number (BN)	mg KOH/g	ASTM D2896	8.5	10.9	8.2	10.3
Visc @ 100°C	cSt	ASTM D445	14.4	13.0	13.9	12.8



Certificate L2367

Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513
Sample No. : WC0891651 **Received** : 12 Jan 2024
Lab Number : 06059932 **Diagnosed** : 16 Jan 2024
Unique Number : 10831314 **Diagnostician** : Wes Davis
Test Package : FLEET

FRESHPOINT
 8801 EXCHANGE DRIVE
 ORLANDO, FL
 US 32809
 Contact: CRAIG EVANS
 evans_craig@sbcglobal.net

To discuss this sample report, contact Customer Service at 1-800-237-1369.

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

T:
F: