



OIL ANALYSIS REPORT

WEAR	NORMAL
CONTAMINATION	NORMAL
FLUID CONDITION	NORMAL

Machine Id
FSP141549
 Component
Diesel Engine
 Fluid
DIESEL ENGINE OIL SAE 15W40 (--- QTS)

RECOMMENDATION

Resample at the next service interval to monitor. Please specify the component make and model with your next sample. Please specify the brand, type, and viscosity of the oil on your next sample.

Test	UOM	Method	Limit/Abn	Current	History1	History2
Sample Number		Client Info		WC0891650	WC0797955	WC0738704
Sample Date		Client Info		09 Jan 2024	14 Apr 2023	06 Oct 2022
Machine Age	mls	Client Info		0	154764	0
Oil Age	mls	Client Info		0	0	0
Filter Age	mls	Client Info		0	0	0
Oil Changed		Client Info		N/A	N/A	Changed
Filter Changed		Client Info		N/A	N/A	Changed
Sample Status				NORMAL	NORMAL	NORMAL

WEAR

All component wear rates are normal.

Iron	ppm	ASTM D5185m	>100	18	26	27
Chromium	ppm	ASTM D5185m	>20	<1	<1	<1
Nickel	ppm	ASTM D5185m	>4	<1	0	0
Titanium	ppm	ASTM D5185m		0	0	0
Silver	ppm	ASTM D5185m	>3	<1	0	0
Aluminum	ppm	ASTM D5185m	>20	2	3	5
Lead	ppm	ASTM D5185m	>40	2	5	17
Copper	ppm	ASTM D5185m	>330	25	2	2
Tin	ppm	ASTM D5185m	>15	<1	1	1
Vanadium	ppm	ASTM D5185m		0	0	0
White Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE

CONTAMINATION







There is no indication of any contamination in the oil.

Silicon	ppm	ASTM D5185m	>25	5	5	6
Potassium	ppm	ASTM D5185m	>20	2	5	28
Fuel		WC Method	>5	<1.0	<1.0	<1.0
Water		WC Method	>0.2	NEG	NEG	NEG
Glycol		WC Method		NEG	NEG	NEG
Soot %	%	*ASTM D7844	>3	0.5	1.6	1.9
Nitration	Abs/cm	*ASTM D7624	>20	7.5	13.4	14.5
Sulfation	Abs/.1mm	*ASTM D7415	>30	19.5	23.9	26.9
Silt	scalar	*Visual	NONE	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.2	NEG	NEG	NEG

FLUID CONDITION

The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

Sodium	ppm	ASTM D5185m	>158	0	2	3
Boron	ppm	ASTM D5185m	250	1	0	<1
Barium	ppm	ASTM D5185m	10	0	0	0
Molybdenum	ppm	ASTM D5185m	100	66	68	66
Manganese	ppm	ASTM D5185m		<1	<1	1
Magnesium	ppm	ASTM D5185m	450	1058	997	1056
Calcium	ppm	ASTM D5185m	3000	1155	1119	1235
Phosphorus	ppm	ASTM D5185m	1150	1110	1069	1118
Zinc	ppm	ASTM D5185m	1350	1283	1309	1380
Sulfur	ppm	ASTM D5185m	4250	3588	3308	3236
Oxidation	Abs/.1mm	*ASTM D7414	>25	15.8	20.9	23.4
Base Number (BN)	mg KOH/g	ASTM D2896	8.5	10.5	10.2	10.6
Visc @ 100°C	cSt	ASTM D445	14.4	13.1	13.4	13.8



Certificate L2367

Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513
Sample No. : WC0891650 **Received** : 12 Jan 2024
Lab Number : 06059935 **Diagnosed** : 16 Jan 2024
Unique Number : 10831317 **Diagnostician** : Wes Davis
Test Package : FLEET

FRESHPOINT
 8801 EXCHANGE DRIVE
 ORLANDO, FL
 US 32809
 Contact: CRAIG EVANS
 evans_craig@sbcglobal.net

To discuss this sample report, contact Customer Service at 1-800-237-1369.

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

T:
F: