



OIL ANALYSIS REPORT

WEAR	NORMAL
CONTAMINATION	NORMAL
FLUID CONDITION	NORMAL

Machine Id
INGERSOLL RAND SD-77F 001723 (S/N 175728)

Component
Diesel Engine

Fluid
CASTROL VECTON 15W40 CK4 (3 GAL)

RECOMMENDATION

Resample at the next service interval to monitor.

Test	UOM	Method	Limit/Abn	Current	History1	History2
Sample Number		Client Info		WC0800510	WC0664812	WC06170549
Sample Date		Client Info		07 Dec 2023	10 Jun 2022	19 Jul 2018
Machine Age	hrs	Client Info		2061	2050	1676
Oil Age	hrs	Client Info		100	374	0
Filter Age	hrs	Client Info		100	374	0
Oil Changed		Client Info		Changed	Changed	Changed
Filter Changed		Client Info		Changed	Changed	Changed
Sample Status				NORMAL	ABNORMAL	NORMAL

WEAR

All component wear rates are normal.

Iron	ppm	ASTM D5185m	>90	23	▲ 78	6
Chromium	ppm	ASTM D5185m	>20	1	5	<1
Nickel	ppm	ASTM D5185m	>2	<1	<1	0
Titanium	ppm	ASTM D5185m	>2	<1	<1	0
Silver	ppm	ASTM D5185m	>2	0	<1	0
Aluminum	ppm	ASTM D5185m	>20	5	▲ 7	1
Lead	ppm	ASTM D5185m	>40	<1	5	<1
Copper	ppm	ASTM D5185m	>330	10	85	<1
Tin	ppm	ASTM D5185m	>15	<1	2	0
Vanadium	ppm	ASTM D5185m		<1	0	0
White Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE

CONTAMINATION







There is no indication of any contamination in the oil.

Silicon	ppm	ASTM D5185m	>25	11	▲ 35	2
Potassium	ppm	ASTM D5185m	>20	2	7	2
Fuel		WC Method	>3.0	<1.0	<1.0	<1.0
Water		WC Method	>0.2	NEG	NEG	NEG
Glycol		WC Method		NEG	NEG	NEG
Soot %	%	*ASTM D7844	>6	0.2	0.5	0.5
Nitration	Abs/cm	*ASTM D7624	>20	8.8	12.2	6.
Sulfation	Abs/.1mm	*ASTM D7415	>30	18.6	24.1	19.
Silt	scalar	*Visual	NONE	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.2	NEG	NEG	NEG

FLUID CONDITION

The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

Sodium	ppm	ASTM D5185m		9	6	2
Boron	ppm	ASTM D5185m		71	73	7
Barium	ppm	ASTM D5185m		1	9	0
Molybdenum	ppm	ASTM D5185m		86	66	51
Manganese	ppm	ASTM D5185m		2	8	<1
Magnesium	ppm	ASTM D5185m		108	332	827
Calcium	ppm	ASTM D5185m		1997	2207	1030
Phosphorus	ppm	ASTM D5185m		1070	975	901
Zinc	ppm	ASTM D5185m		1226	1244	989
Sulfur	ppm	ASTM D5185m		3500	3706	4027
Oxidation	Abs/.1mm	*ASTM D7414	>25	14.3	22.2	15.
Base Number (BN)	mg KOH/g	ASTM D2896	10	7.0	7.6	7.73
Visc @ 100°C	cSt	ASTM D445	15.5	13.2	13.3	13.77



Certificate L2367

Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513
Sample No. : WC0800510 **Recieved** : 12 Jan 2024
Lab Number : 06060112 **Diagnosed** : 16 Jan 2024
Unique Number : 10831494 **Diagnostician** : Wes Davis
Test Package : CONST (Additional Tests: TBN)

To discuss this sample report, contact Customer Service at 1-800-237-1369.

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

CJ MILLER LLC
 2903 DEDE RD
 FINKSBURG, MD
 US 21048

Contact: JOE ROSS
 jross@cjmillerllc.com
 T: (410)239-8006
 F: (410)239-1051