



**PERFORMANCE
UNDER
PRESSURE**

OIL ANALYSIS REPORT

WEAR	NORMAL
CONTAMINATION	NORMAL
FLUID CONDITION	NORMAL

Machine Id
LIM4_U46 LIM4_U46_M46

Component
Lube System

Fluid
ROYAL PURPLE SYNFILM GT 32 (20 GAL)

RECOMMENDATION

Resample at the next service interval to monitor. Sample submitted as hydraulic. Confirm component type.

Test	UOM	Method	Limit/Abn	Current	History1	History2
Sample Number		Client Info		RP0029463	RP0029414	RP0021255
Sample Date		Client Info		08 Jan 2024	24 Oct 2023	18 Jul 2023
Machine Age	hrs	Client Info		0	0	0
Oil Age	hrs	Client Info		0	0	0
Filter Age	hrs	Client Info		0	0	0
Oil Changed		Client Info		N/A	N/A	N/A
Filter Changed		Client Info		N/A	N/A	N/A
Sample Status				NORMAL	NORMAL	NORMAL

WEAR

All component wear rates are normal.

Iron	ppm	ASTM D5185m	>20	0	0	<1
Chromium	ppm	ASTM D5185m	>20	<1	0	0
Nickel	ppm	ASTM D5185m	>20	0	0	0
Titanium	ppm	ASTM D5185m		0	0	0
Silver	ppm	ASTM D5185m		0	0	0
Aluminum	ppm	ASTM D5185m	>20	2	<1	<1
Lead	ppm	ASTM D5185m	>20	1	12	9
Copper	ppm	ASTM D5185m	>20	1	11	10
Tin	ppm	ASTM D5185m	>20	0	<1	<1
Vanadium	ppm	ASTM D5185m		0	0	0
White Metal	scalar	*Visual	NONE	NONE	NONE	LIGHT
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE

CONTAMINATION













There is no indication of any contamination in the oil.

Silicon	ppm	ASTM D5185m	>15	2	2	2
Potassium	ppm	ASTM D5185m	>20	1	1	0
Water	%	ASTM D6304	>0.05	0.018	0.018	0.016
ppm Water	ppm	ASTM D6304	>500	185	185.8	163.9
Particles >4µm		ASTM D7647	>5000	9949	---	---
Particles >6µm		ASTM D7647	>1300	939	---	---
Particles >14µm		ASTM D7647	>160	31	---	---
Particles >21µm		ASTM D7647	>40	6	---	---
Particles >38µm		ASTM D7647	>10	0	---	---
Particles >71µm		ASTM D7647	>3	0	---	---
Oil Cleanliness		ISO 4406 (c)	>19/17/14	20/17/12	---	---
Silt	scalar	*Visual	NONE	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.05	NEG	NEG	NEG

FLUID CONDITION

The AN level is acceptable for this fluid. The condition of the oil is suitable for further service.

Sodium	ppm	ASTM D5185m		0	2	1
Boron	ppm	ASTM D5185m		0	0	0
Barium	ppm	ASTM D5185m		0	0	0
Molybdenum	ppm	ASTM D5185m		0	0	0
Manganese	ppm	ASTM D5185m		0	0	0
Magnesium	ppm	ASTM D5185m		86	40	51
Calcium	ppm	ASTM D5185m		3	0	1
Phosphorus	ppm	ASTM D5185m		36	0	2
Zinc	ppm	ASTM D5185m		0	<1	0
Acid Number (AN)	mg KOH/g	ASTM D8045		0.33	0.34	0.35
Visc @ 40°C	cSt	ASTM D445	32	32.2	33.4	33.4



Certificate L2367

Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513
Sample No. : RP0029463
Lab Number : 06060226
Unique Number : 10831608
Test Package : PLANT

Received : 12 Jan 2024
Diagnosed : 16 Jan 2024
Diagnostician : Doug Bogart

ENERGY TRANSFER - LIMA
 1520 BUCKEYE RD
 LIMA, OH
 US 45804

Contact: ANDREW WYDERKA
 andrew.wyderka@energytransfer.com

T: (419)618-1505

F:

To discuss this sample report, contact Customer Service at 1-800-237-1369.

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)