



WEAR	NORMAL
CONTAMINATION	MARGINAL
FLUID CONDITION	NORMAL



Machine Id
775M
Component
Diesel Engine
Fluid
PETRO CANADA DURON SHP 15W40 (--- GAL)

RECOMMENDATION

We recommend you service the filters on this component. Resample at the next service interval to monitor.

Test	UOM	Method	Limit/Abn	Current	History1	History2
Sample Number		Client Info		GFL0110019	GFL0104190	GFL0059302
Sample Date		Client Info		11 Jan 2024	02 Jan 2024	07 Dec 2023
Machine Age	hrs	Client Info		7409	7356	7242
Oil Age	hrs	Client Info		7295	114	7242
Filter Age	hrs	Client Info		0	0	0
Oil Changed		Client Info		N/A	N/A	Changed
Filter Changed		Client Info		N/A	N/A	Changed
Sample Status				MARGINAL	ABNORMAL	NORMAL

WEAR

All component wear rates are normal.

Iron	ppm	ASTM D5185m	>90	70	46	40
Chromium	ppm	ASTM D5185m	>20	2	1	2
Nickel	ppm	ASTM D5185m	>2	<1	<1	0
Titanium	ppm	ASTM D5185m	>2	0	<1	0
Silver	ppm	ASTM D5185m	>2	0	0	0
Aluminum	ppm	ASTM D5185m	>20	6	5	3
Lead	ppm	ASTM D5185m	>40	4	2	1
Copper	ppm	ASTM D5185m	>330	2	2	3
Tin	ppm	ASTM D5185m	>15	<1	<1	0
Vanadium	ppm	ASTM D5185m		0	<1	0
White Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE

CONTAMINATION








There is an abnormal amount of solids and carbon present in the oil.

Silicon	ppm	ASTM D5185m	>25	10	6	7
Potassium	ppm	ASTM D5185m	>20	3	4	<1
Fuel		WC Method	>3.0	<1.0	<1.0	<1.0
Water		WC Method	>0.2	NEG	NEG	NEG
Glycol		WC Method		NEG	NEG	NEG
Soot %	%	*ASTM D7844	>6	▲ 3.9	▲ 3.6	1
Nitration	Abs/cm	*ASTM D7624	>20	17.2	15.8	13.3
Sulfation	Abs/.1mm	*ASTM D7415	>30	34.9	32.8	24.5
Silt	scalar	*Visual	NONE	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.2	NEG	NEG	NEG

FLUID CONDITION

The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

Sodium	ppm	ASTM D5185m		7	9	37
Boron	ppm	ASTM D5185m	0	4	<1	<1
Barium	ppm	ASTM D5185m	0	0	7	0
Molybdenum	ppm	ASTM D5185m	60	63	43	53
Manganese	ppm	ASTM D5185m	0	<1	<1	<1
Magnesium	ppm	ASTM D5185m	1010	990	699	951
Calcium	ppm	ASTM D5185m	1070	1087	832	1028
Phosphorus	ppm	ASTM D5185m	1150	1131	583	1003
Zinc	ppm	ASTM D5185m	1270	1354	996	1196
Sulfur	ppm	ASTM D5185m	2060	2702	1748	2718
Oxidation	Abs/.1mm	*ASTM D7414	>25	30.1	27.4	24.8
Base Number (BN)	mg KOH/g	ASTM D2896	9.8	5.0	▲ 0.0	7.1
Visc @ 100°C	cSt	ASTM D445	15.4	16.3	16.2	13.4



Certificate L2367

Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513
Sample No. : GFL0110019 **Received** : 16 Jan 2024
Lab Number : 06060757 **Diagnosed** : 17 Jan 2024
Unique Number : 10832139 **Diagnostician** : Jonathan Hester
Test Package : FLEET

GFL Environmental - 410 - Michigan West
 39000 Van Born Rd
 Wayne, MI
 US 48184
 Contact: Belal Dgheish
 bdgheish@gflenv.com
 T: (734)714-2340
 F:

To discuss this sample report, contact Customer Service at 1-800-237-1369.

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)