



OIL ANALYSIS REPORT

WEAR	NORMAL
CONTAMINATION	NORMAL
FLUID CONDITION	NORMAL

Machine Id
813511
 Component
Diesel Engine
 Fluid
MOBIL DELVAC EXTREME 15W40 (--- GAL)

RECOMMENDATION

Resample at the next service interval to monitor.

Test	UOM	Method	Limit/Abn	Current	History1	History2
Sample Number		Client Info		RPL0008100	RPL0008036	RPL0008001
Sample Date		Client Info		08 Jan 2024	08 Mar 2023	28 Jun 2022
Machine Age	hrs	Client Info		13116	331641	4702
Oil Age	hrs	Client Info		427	15431	528
Filter Age	hrs	Client Info		427	15431	528
Oil Changed		Client Info		Changed	Not Changd	Changed
Filter Changed		Client Info		Changed	Not Changd	Changed
Sample Status				NORMAL	ABNORMAL	NORMAL

WEAR

All component wear rates are normal.

Iron	ppm	ASTM D5185m	>100	31	29	25
Chromium	ppm	ASTM D5185m	>20	<1	2	2
Nickel	ppm	ASTM D5185m	>4	0	<1	0
Titanium	ppm	ASTM D5185m		9	0	0
Silver	ppm	ASTM D5185m	>3	0	0	<1
Aluminum	ppm	ASTM D5185m	>20	8	5	5
Lead	ppm	ASTM D5185m	>40	3	3	8
Copper	ppm	ASTM D5185m	>330	<1	▲ 380	1
Tin	ppm	ASTM D5185m	>15	1	▲ 37	1
Vanadium	ppm	ASTM D5185m		<1	0	0
White Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE

CONTAMINATION







There is no indication of any contamination in the oil.

Silicon	ppm	ASTM D5185m	>25	9	5	7
Potassium	ppm	ASTM D5185m	>20	5	3	2
Fuel		WC Method	>5	<1.0	<1.0	<1.0
Water		WC Method	>0.2	NEG	NEG	NEG
Glycol		WC Method		NEG	0.0	NEG
Soot %	%	*ASTM D7844	>3	0.5	0.4	0.5
Nitration	Abs/cm	*ASTM D7624	>20	9.0	9.7	14.9
Sulfation	Abs/.1mm	*ASTM D7415	>30	21.0	21.6	30.9
Silt	scalar	*Visual	NONE	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.2	NEG	NEG	NEG

FLUID CONDITION

The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

Sodium	ppm	ASTM D5185m		<1	<1	1
Boron	ppm	ASTM D5185m		15	13	8
Barium	ppm	ASTM D5185m		0	2	0
Molybdenum	ppm	ASTM D5185m		60	59	64
Manganese	ppm	ASTM D5185m		<1	<1	<1
Magnesium	ppm	ASTM D5185m		953	808	877
Calcium	ppm	ASTM D5185m		1159	1185	1336
Phosphorus	ppm	ASTM D5185m		1133	974	995
Zinc	ppm	ASTM D5185m		1342	1196	1251
Sulfur	ppm	ASTM D5185m		3334	2883	3252
Oxidation	Abs/.1mm	*ASTM D7414	>25	16.3	17.6	32.4
Base Number (BN)	mg KOH/g	ASTM D2896	10.3	8.5	7.7	5.4
Visc @ 100°C	cSt	ASTM D445	14.3	13.2	13.0	14.3



Certificate L2367

Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513
Sample No. : RPL0008100 **Received** : 16 Jan 2024
Lab Number : 06060908 **Diagnosed** : 17 Jan 2024
Unique Number : 10832290 **Diagnostician** : Wes Davis
Test Package : FLEET

RTL PACLEASE - 7017 - Oklahoma City
 8700 West I-40
 Oklahoma City, OK
 US 73128
 Contact: TECHNICIAN ACCOUNT
 catherine.anastasio@wearcheck.com
 T:
 F:

To discuss this sample report, contact Customer Service at 1-800-237-1369.

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)