



OIL ANALYSIS REPORT

WEAR	NORMAL
CONTAMINATION	NORMAL
FLUID CONDITION	NORMAL



Area
PCS - PORTABLE CRUSHING SERVICES
Machine Id
KOMATSU WA470 LD05 - PCS
Component
Hydraulic System
Fluid
STP HYDRO ISO AW 46 (--- GAL)

RECOMMENDATION

Resample at the next service interval to monitor.

Test	UOM	Method	Limit/Abn	Current	History1	History2
Sample Number		Client Info		KL0013957	KL0013098	KL0009663
Sample Date		Client Info		09 Jan 2024	03 Oct 2023	29 Jun 2023
Machine Age	hrs	Client Info		7844	7322	7123
Oil Age	hrs	Client Info		3919	3397	3198
Filter Age	hrs	Client Info		3919	3397	3198
Oil Changed		Client Info		Not Changd	Not Changd	Not Changd
Filter Changed		Client Info		Not Changd	Not Changd	Not Changd
Sample Status				NORMAL	NORMAL	NORMAL

WEAR

All component wear rates are normal.

Iron	ppm	ASTM D5185m	>20	<1	0	0
Chromium	ppm	ASTM D5185m	>10	0	0	0
Nickel	ppm	ASTM D5185m	>10	0	0	0
Titanium	ppm	ASTM D5185m		0	0	0
Silver	ppm	ASTM D5185m		0	0	0
Aluminum	ppm	ASTM D5185m	>10	0	<1	<1
Lead	ppm	ASTM D5185m	>10	0	0	0
Copper	ppm	ASTM D5185m	>75	<1	<1	<1
Tin	ppm	ASTM D5185m	>10	0	<1	0
Vanadium	ppm	ASTM D5185m		0	0	<1
White Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE

CONTAMINATION










The system cleanliness is acceptable for your target ISO 4406 cleanliness code. The system and fluid cleanliness is acceptable.

Silicon	ppm	ASTM D5185m	>20	1	1	1
Potassium	ppm	ASTM D5185m	>20	0	<1	<1
Water		WC Method	>0.1	NEG	NEG	NEG
Particles >4µm		ASTM D7647		1857	1415	3353
Particles >6µm		ASTM D7647	>1300	147	138	373
Particles >14µm		ASTM D7647	>160	18	14	37
Particles >21µm		ASTM D7647	>40	6	5	11
Particles >38µm		ASTM D7647	>10	0	2	1
Particles >71µm		ASTM D7647	>3	0	1	0
Oil Cleanliness		ISO 4406 (c)	>17/14	14/11	14/11	16/12
Silt	scalar	*Visual	NONE	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.1	NEG	NEG	NEG

FLUID CONDITION

The AN level is acceptable for this fluid. The condition of the oil is suitable for further service.

Sodium	ppm	ASTM D5185m		<1	0	<1
Boron	ppm	ASTM D5185m		0	<1	0
Barium	ppm	ASTM D5185m		0	0	<1
Molybdenum	ppm	ASTM D5185m		<1	0	<1
Manganese	ppm	ASTM D5185m		0	0	0
Magnesium	ppm	ASTM D5185m		0	15	14
Calcium	ppm	ASTM D5185m		96	110	111
Phosphorus	ppm	ASTM D5185m		301	302	305
Zinc	ppm	ASTM D5185m		341	325	319
Sulfur	ppm	ASTM D5185m		1335	1011	1193
Acid Number (AN)	mg KOH/g	ASTM D8045		0.36	0.31	0.31
Visc @ 40°C	cSt	ASTM D445		45.8	47.6	50.3



Certificate L2367

Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513
Sample No. : KL0013957 **Received** : 16 Jan 2024
Lab Number : 06060992 **Diagnosed** : 17 Jan 2024
Unique Number : 10832374 **Diagnostician** : Jonathan Hester
Test Package : MOB 2

PIKES PEAK PERFORMANCE PRODUCTS
 7888 BULLET RD
 PEYTON, CO
 US 80831
 Contact: SCOTT RIGGS
 rriggs.pikespeakperformance@gmail.com
 T: (303)434-0126
 F: x:

To discuss this sample report, contact Customer Service at 1-800-237-1369.

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)