



OIL ANALYSIS REPORT

WEAR	NORMAL
CONTAMINATION	NORMAL
FLUID CONDITION	NORMAL

Area
WCLSNC
Machine Id
QC230801DE
Component
Diesel Engine
Fluid
PETRO CANADA DURON SHP 15W40 (--- GAL)

RECOMMENDATION

Resample at the next service interval to monitor.

Test	UOM	Method	Limit/Abn	Current	History1	History2
Sample Number		Client Info		WC0895269	WC0895265	WC0895264
Sample Date		Client Info		16 Jan 2024	12 Jan 2024	11 Jan 2024
Machine Age	hrs	Client Info		0	0	0
Oil Age	hrs	Client Info		0	0	0
Filter Age	hrs	Client Info		0	0	0
Oil Changed		Client Info		N/A	N/A	N/A
Filter Changed		Client Info		N/A	N/A	N/A
Sample Status				NORMAL	NORMAL	NORMAL

WEAR

All component wear rates are normal.

Iron	ppm	ASTM D5185m	>11	5	4	5
Chromium	ppm	ASTM D5185m	>3	<1	<1	0
Nickel	ppm	ASTM D5185m	>2	0	2	0
Titanium	ppm	ASTM D5185m	>2	0	0	0
Silver	ppm	ASTM D5185m	>2	0	<1	0
Aluminum	ppm	ASTM D5185m	>5	2	3	1
Lead	ppm	ASTM D5185m	>2	0	<1	<1
Copper	ppm	ASTM D5185m	>7	6	4	4
Tin	ppm	ASTM D5185m	>2	0	0	0
Vanadium	ppm	ASTM D5185m		0	<1	0
White Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE

CONTAMINATION














There is no indication of any contamination in the oil.

Silicon	ppm	ASTM D5185m	>14	3	5	6
Potassium	ppm	ASTM D5185m	>20	0	1	2
Fuel	%	ASTM D3524	>4.1	2.6	2.7	2.7
Water	%	ASTM D6304	>0.2	NEG	NEG	NEG
Glycol	%	*ASTM D2982		NEG	NEG	NEG
Soot %	%	*ASTM D7844	>0.3	0.1	0.1	0.1
Nitration	Abs/cm	*ASTM D7624	>10.8	10.3	10.2	10.3
Sulfation	Abs/.1mm	*ASTM D7415	>20.8	20.0	20.2	20.3
Silt	scalar	*Visual	NONE	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.2	NEG	NEG	NEG

FLUID CONDITION

The BN result indicates that there is suitable alkalinity remaining in the oil. The AN level is acceptable for this fluid. The condition of the oil is suitable for further service.

Sodium	ppm	ASTM D5185m	>13	5	5	6
Boron	ppm	ASTM D5185m	0	0	0	5
Barium	ppm	ASTM D5185m	0	0	0	0
Molybdenum	ppm	ASTM D5185m	60	50	47	46
Manganese	ppm	ASTM D5185m	0	<1	<1	0
Magnesium	ppm	ASTM D5185m	1010	539	566	528
Calcium	ppm	ASTM D5185m	1070	1453	1441	1454
Phosphorus	ppm	ASTM D5185m	1150	679	675	627
Zinc	ppm	ASTM D5185m	1270	924	965	945
Sulfur	ppm	ASTM D5185m	2060	2222	2384	2207
Oxidation	Abs/.1mm	*ASTM D7414	>17.9	17.4	17.2	17.4
Acid Number (AN)	mg KOH/g	ASTM D8045	3.2	0.87	0.34	0.662
Base Number (BN)	mg KOH/g	ASTM D2896	9.8	7.89	7.37	7.59
Visc @ 40°C	cSt	ASTM D445	113.9	98.3	98.4	98.2
Visc @ 100°C	cSt	ASTM D445	15.4	13.3	13.3	13.3
Viscosity Index (VI)	Scale	ASTM D2270	142	134	133	134



Certificate L2367

Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513
Sample No. : WC0895269 **Received** : 16 Jan 2024
Lab Number : 06061352 **Diagnosed** : 18 Jan 2024
Unique Number : 10832734 **Diagnostician** : Jonathan Hester

WEARCHECK LUBRICATION SERVICES QA ACCOUNT

501 Madison Ave
 Cary, NC
 US 27513

Test Package : MOB 2 (Additional Tests: FuelDilution, Glycol, KF, KV40, PercentFuel, VI)
 Contact: WCLS CARY NC

To discuss this sample report, contact Customer Service at 1-800-237-1369.

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

T: (919)379-4102

F: (919)379-4050