**WEAR CONTAMINATION FLUID CONDITION**  **NORMAL NORMAL NORMAL** 

## **JOHN DEERE 1025R 1LV1025RPNN842278**

Component Transmission (Manual)

IOHN DEERE HY-GARD HYD/TRANS LOW VIS (--- GAL)

JOHN DEERE HY-GARD HYD/TRANS LOW VIS	6 ( GAL)						
RECOMMENDATION	Test	UOM	Method	Limit/Abn	Current	History1	History2
Resample at the next service interval to monitor.	Sample Number		Client Info		JR0137481		
	Sample Date		Client Info		11 Jan 2024		
	Machine Age	hrs	Client Info		66		
	Oil Age	hrs	Client Info		66		
	Filter Age	hrs	Client Info		60		
	Oil Changed		Client Info		Not Changd		
	Filter Changed		Client Info		Not Changd		
	Sample Status				NORMAL		
WEAR	DO.		ACTM DO104	٥٦	40		
WEAR	PQ		ASTM D8184		18		
All component wear rates are normal.	Iron	ppm	ASTM D5185m		16		
	Chromium	ppm	ASTM D5185m		<1		
	Nickel	ppm	ASTM D5185m	>5	0		
	Titanium	ppm	ASTM D5185m	. 7	0		
	Silver	ppm	ASTM D5185m		<1		
	Aluminum	ppm	ASTM D5185m		4		
	Lead	ppm	ASTM D5185m		<1		
	Copper	ppm	ASTM D5185m		13		
	Tin	ppm	ASTM D5185m	>10	0		
	Vanadium	ppm	ASTM D5185m	NONE	0 NONE		
	White Metal	scalar	*Visual	NONE	NONE		
	Yellow Metal	scalar	*Visual	NONE	NONE		
CONTAMINATION	Silicon	ppm	ASTM D5185m	>125	13		
There is no indication of any contamination in the fluid.	Potassium	ppm	ASTM D5185m	>20	2		
	Water		WC Method	>0.1	NEG		
	Silt	scalar	*Visual	NONE	NONE		
	Debris	scalar	*Visual	NONE	NONE		
	Sand/Dirt	scalar	*Visual	NONE	NONE		
	Appearance	scalar	*Visual	NORML	NORML		
	Odor	scalar	*Visual	NORML	NORML		
	Emulsified Water	scalar	*Visual	>0.1	NEG		
FLUID CONDITION	O - alla		AOTA DEADE				
FLUID CONDITION	Sodium	ppm	ASTM D5185m		<1		
The condition of the fluid is acceptable for the time in service.	Boron	ppm	ASTM D5185m		0		
	Barium	ppm	ASTM D5185m		3		
	Molybdenum	ppm	ASTM D5185m		0		
	Manganese	ppm	ASTM D5185m		2		
	Magnesium	ppm	ASTM D5185m		100		
	Calcium	ppm	ASTM D5185m		3302		
	Phosphorus	ppm	ASTM D5185m		1013		
	Zinc	ppm	ASTM D5185m		1222		
	Sulfur	ppm	ASTM D5185m	00	3477		
	Visc @ 40°C	cSt	ASTM D445	32	33.6		





Certificate L2367

Report Id: JAMWIL [WUSCAR] 06061409 (Generated: 01/17/2024 14:06:52) Rev: 1

Laboratory Sample No. Lab Number **Unique Number** 

: JR0137481 : 06061409

: 10832791

: WearCheck USA - 501 Madison Ave., Cary, NC 27513 Recieved : 16 Jan 2024 Diagnosed

: 17 Jan 2024 Diagnostician : Wes Davis

Test Package : MOBCE ( Additional Tests: PQ ) To discuss this sample report, contact Customer Service at 1-800-237-1369.

288 WESTGATE DRIVE WILKESBORO, NC US 28697 Contact: James Blackburn

JRE - WILKESBORO

jblackburn@jamesriverequipment.com T: (336)973-8201

\* - Denotes test methods that are outside of the ISO 17025 scope of accreditation. Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

F: (336)973-8496