



WEAR	NORMAL
CONTAMINATION	NORMAL
FLUID CONDITION	NORMAL

Area

[HERITAGE SITE]

Machine Id

JOHN DEERE 350G 1FF350GXVMF815188

Component

Left Final Drive

Fluid

JOHN DEERE GL-5 80W90 (--- GAL)

RECOMMENDATION

Resample at the next service interval to monitor.

Test	UOM	Method	Limit/Abn	Current	History1	History2
Sample Number		Client Info		JR0184650	JR0169958	JR0176445
Sample Date		Client Info		08 Jan 2024	23 Aug 2023	26 Jun 2023
Machine Age	hrs	Client Info		4476	4002	3881
Oil Age	hrs	Client Info		0	0	2088
Filter Age	hrs	Client Info		0	0	0
Oil Changed		Client Info		Not Changd	Changed	N/A
Filter Changed		Client Info		N/A	N/A	N/A
Sample Status				NORMAL	NORMAL	NORMAL

WEAR

All component wear rates are normal.

PQ		ASTM D8184	>1250	68	76	168
Iron	ppm	ASTM D5185m	>750	55	79	330
Chromium	ppm	ASTM D5185m	>9	<1	<1	4
Nickel	ppm	ASTM D5185m	>10	0	<1	1
Titanium	ppm	ASTM D5185m		0	<1	<1
Silver	ppm	ASTM D5185m		0	0	0
Aluminum	ppm	ASTM D5185m	>40	1	1	3
Lead	ppm	ASTM D5185m	>15	0	0	0
Copper	ppm	ASTM D5185m	>40	1	<1	<1
Tin	ppm	ASTM D5185m	>10	0	0	0
Vanadium	ppm	ASTM D5185m		0	0	<1
White Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE

CONTAMINATION







There is no indication of any contamination in the oil.

Silicon	ppm	ASTM D5185m	>75	4	8	22
Potassium	ppm	ASTM D5185m	>20	0	<1	3
Water		WC Method	>0.075	NEG	NEG	NEG
Silt	scalar	*Visual	NONE	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.075	NEG	NEG	NEG

FLUID CONDITION

The condition of the oil is acceptable for the time in service.

Sodium	ppm	ASTM D5185m	>51	0	0	2
Boron	ppm	ASTM D5185m		2	27	4
Barium	ppm	ASTM D5185m		0	0	3
Molybdenum	ppm	ASTM D5185m		0	1	1
Manganese	ppm	ASTM D5185m		1	<1	3
Magnesium	ppm	ASTM D5185m		7	3	5
Calcium	ppm	ASTM D5185m		33	25	39
Phosphorus	ppm	ASTM D5185m		953	426	243
Zinc	ppm	ASTM D5185m		20	10	28
Sulfur	ppm	ASTM D5185m		21187	18713	14714
Visc @ 40°C	cSt	ASTM D445		139	138	139



Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513
Sample No. : JR0184650 **Received** : 16 Jan 2024
Lab Number : 06061457 **Diagnosed** : 17 Jan 2024
Unique Number : 10832839 **Diagnostician** : Sean Felton
Test Package : CONST (Additional Tests: PQ)

JRE - STEPHENSON
 245 YARDMASTER COURT
 STEPHENSON, VA
 US 22656-1761
 Contact: PHIL DAUGHERTY
 pdaugherty@jamesriverequipment.com
 T: x:
 F: (540)693-2588

Certificate L2367
 To discuss this sample report, contact Customer Service at 1-800-237-1369.
 * - Denotes test methods that are outside of the ISO 17025 scope of accreditation.
 Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)