WEAR CONTAMINATION FLUID CONDITION

NORMAL NORMAL NORMAL

[STK ENTERPRISES]

SENNEBOGEN 728M 728.0.1043

Component Pump Drive

{not provided} (GAL)							
RECOMMENDATION	Test	UOM	Method	Limit/Abn	Current	History1	History2
Resample at the next service interval to monitor. Please specify the brand, type, and viscosity of the oil on your next sample.	Sample Number		Client Info		JR0195604		
	Sample Date		Client Info		05 Jan 2024		
	Machine Age	hrs	Client Info		982		
	Oil Age	hrs	Client Info		0		
	Filter Age	hrs	Client Info		0		
	Oil Changed		Client Info		Not Changd		
	Filter Changed		Client Info		N/A		
	Sample Status				NORMAL		
WEAR	PQ		ASTM D8184		22		
All component wear rates are normal.	Iron	ppm	ASTM D5185m	>500	32		
	Chromium	ppm	ASTM D5185m	>15	<1		
	Nickel	ppm	ASTM D5185m	>10	0		
	Titanium	ppm	ASTM D5185m		0		
	Silver	ppm	ASTM D5185m		0		
	Aluminum	ppm	ASTM D5185m	>20	<1		
	Lead	ppm	ASTM D5185m		0		
	Copper	ppm	ASTM D5185m		1		
	Tin	ppm	ASTM D5185m	>4	0		
	Vanadium	ppm	ASTM D5185m	NONE	0		
	White Metal	scalar	*Visual	NONE	NONE		
	Yellow Metal	scalar	*Visual	NONE	NONE		
CONTAMINATION There is no indication of any contamination in the oil.	Silicon	ppm	ASTM D5185m	>75	6		
	Potassium	ppm	ASTM D5185m	>20	0		
	Water		WC Method	>0.2	NEG		
	Silt	scalar	*Visual	NONE	NONE		
	Debris	scalar	*Visual	NONE	NONE		
	Sand/Dirt	scalar	*Visual	NONE	NONE		
	Appearance	scalar	*Visual	NORML	NORML		
	Odor	scalar	*Visual	NORML	NORML		
	Emulsified Water	scalar	*Visual	>0.2	NEG		
FLUID CONDITION	Sodium	ppm	ASTM D5185m		0		
The condition of the oil is acceptable for the time in service.	Boron	ppm	ASTM D5185m		5		
	Barium	ppm	ASTM D5185m		4		
	Molybdenum	ppm	ASTM D5185m		0		
	Manganese	ppm	ASTM D5185m		2		
	Magnesium	ppm	ASTM D5185m		4		
	Calcium	ppm	ASTM D5185m		26		
	Phosphorus	ppm	ASTM D5185m		658		
	Zinc	ppm	ASTM D5185m		44		
	Sulfur	ppm	ASTM D5185m		4513		
	Visc @ 40°C	cSt	ASTM D445		127		





Certificate L2367

Laboratory Sample No. Lab Number

Unique Number

: JR0195604 : 06061462 : 10832844 Test Package : CONST (Additional Tests: PQ)

: WearCheck USA - 501 Madison Ave., Cary, NC 27513 Recieved : 16 Jan 2024 : 17 Jan 2024 Diagnosed Diagnostician : Sean Felton

To discuss this sample report, contact Customer Service at 1-800-237-1369.

245 YARDMASTER COURT STEPHENSON, VA US 22656-1761 Contact: PHIL DAUGHERTY

JRE - STEPHENSON

pdaugherty@jamesriverequipment.com

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation. Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

T: x: F: (540)693-2588