

WEAR CONTAMINATION **FLUID CONDITION**

NORMAL NORMAL NORMAL



LIEBHERR LH40M 122207-1215


Front Differential Fluid GEAR OIL SAE 80W90 (GAL))						
RECOMMENDATION	Test	UOM	Method	Limit/Abn	Current	History1	History2
Resample at the next service interval to monitor. The fluid was not specified, however, a fluid match indicates that this fluid is (GENERIC) GEAR OIL SAE 80W90. Please confirm.	Sample Number		Client Info		LH0273221	LH0244668	
	Sample Date		Client Info		08 Jan 2024	17 May 2023	
	Machine Age	hrs	Client Info		3977	2962	
	Oil Age	hrs	Client Info		0	0	
	Filter Age	hrs	Client Info		0	0	
	Oil Changed		Client Info		Changed	Changed	
	Filter Changed		Client Info		N/A	Changed	
	Sample Status				NORMAL	NORMAL	
WEAR	Iron	ppm	ASTM D5185m	<150	2	2	
	Chromium	ppm	ASTM D5185m		<1	0	
All component wear rates are normal.	Nickel	ppm	ASTM D5185m		0	0	
	Titanium	ppm	ASTM D5185m	>10	<1	0	
	Silver	ppm	ASTM D5185m		0	0	
	Aluminum	ppm	ASTM D5185m	>5	2	0	
	Lead	ppm	ASTM D5185m		0	0	
	Copper	ppm	ASTM D5185m	>125	10	8	
	Tin	ppm	ASTM D5185m	>5	<1	0	
	Vanadium	ppm	ASTM D5185m		0	0	
	White Metal	scalar	*Visual	NONE	NONE	NONE	
	Yellow Metal	scalar	*Visual	NONE	NONE	NONE	
CONTAMINATION	Silicon	ppm	ASTM D5185m	> 20	<1	<1	
There is no indication of any contamination in the oil.	Potassium	ppm	ASTM D5185m		<1	<1	
	Water	РРШ		>0.2	NEG	NEG	
	Silt	scalar	*Visual	NONE	NONE	NONE	
	Debris	scalar	*Visual	NONE	NONE	NONE	
	Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	
	Appearance	scalar	*Visual	NORML	NORML	NORML	
	Odor	scalar	*Visual	NORML	NORML	NORML	
	Emulsified Water	scalar	*Visual	>0.2	NEG	NEG	
FLUID CONDITION	Sodium	ppm	ASTM D5185m	>170	0	2	
The condition of the oil is acceptable for the time in service.	Boron	ppm	ASTM D5185m	400	0	0	
	Barium	ppm	ASTM D5185m		0	0	
	Molybdenum	ppm	ASTM D5185m	12	<1	0	
	Manganese	ppm	ASTM D5185m		0	0	
	Magnesium	ppm	ASTM D5185m		0	<1	
	Calcium	ppm	ASTM D5185m		7	4	
	Phosphorus	ppm	ASTM D5185m		2287	2440	
	Zinc	ppm	ASTM D5185m		0	0	
	Sulfur	ppm	ASTM D5185m	22500	27959	25056	


Visc @ 40°C


ASTM D445 143


184

187













Certificate L2367

Laboratory Sample No. Lab Number

Unique Number : 10832928 Test Package : CONST

: LH0273221 : 06061546

: WearCheck USA - 501 Madison Ave., Cary, NC 27513 Recieved : 16 Jan 2024 : 17 Jan 2024 Diagnosed Diagnostician : Wes Davis

To discuss this sample report, contact Customer Service at 1-800-237-1369. * - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

RECO EQUIPMENT INC.

1040 REED DRIVE MONROE, OH US 45050 Contact: Eric Hansen

ehansen@recoequip.com T: (513)539-5255

F: (513)539-5256