


WEAR CONTAMINATION **FLUID CONDITION**


NORMAL NORMAL NORMAL





LIEBHERR LH40M 122207-1215

Splitter Box GEAR OIL SAE 80W90 (GAL	.)				.,		
RECOMMENDATION	Test	UOM	Method	Limit/Abn	Current	History1	History2
Resample at the next service interval to monitor. The fluid was not specified, however, a fluid match indicates that this fluid is (GENERIC) GEAR OIL SAE 80W90. Please confirm.	Sample Number		Client Info		LH0273222	LH0244671	
	Sample Date		Client Info		08 Jan 2024	17 May 2023	
	Machine Age	hrs	Client Info		3977	2962	
	Oil Age	hrs	Client Info		0	0	
	Filter Age	hrs	Client Info		0	0	
	Oil Changed		Client Info		Changed	Changed	
	Filter Changed		Client Info		N/A	Changed	
	Sample Status				NORMAL	NORMAL	
WEAR	Iron	ppm	ASTM D5185m	>100	17	10	
All component wear rates are normal.	Chromium	ppm	ASTM D5185m	>5	<1	0	
	Nickel	ppm	ASTM D5185m	>5	0	0	
	Titanium	ppm	ASTM D5185m		<1	0	
	Silver	ppm	ASTM D5185m		0	0	
	Aluminum	ppm	ASTM D5185m	>20	2	0	
	Lead	ppm	ASTM D5185m	>30	0	0	
	Copper	ppm	ASTM D5185m		2	1	
	Tin	ppm	ASTM D5185m	>10	<1	0	
	Vanadium	ppm	ASTM D5185m		0	0	
	White Metal	scalar	*Visual	NONE	NONE	NONE	
	Yellow Metal	scalar	*Visual	NONE	NONE	NONE	
CONTAMINATION	Silicon	ppm	ASTM D5185m	>30	<1	<1	
There is no indication of any contamination in the oil.	Potassium	ppm	ASTM D5185m	>20	2	3	
	Water		WC Method	>0.1	NEG	NEG	
	Silt	scalar	*Visual	NONE	NONE	NONE	
	Debris	scalar	*Visual	NONE	NONE	NONE	
	Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	
	Appearance	scalar	*Visual	NORML	NORML	NORML	
	Odor	scalar	*Visual	NORML	NORML	NORML	
	Emulsified Water	scalar	*Visual	>0.1	NEG	NEG	
FLUID CONDITION	Sodium	ppm	ASTM D5185m	>170	0	2	
The condition of the oil is acceptable for the time in service.	Boron	ppm	ASTM D5185m	400	<1	0	
	Barium	ppm	ASTM D5185m	200	0	0	
	Molybdenum	ppm	ASTM D5185m	12	<1	0	
	Manganese	ppm	ASTM D5185m		<1	<1	
	Magnesium	ppm	ASTM D5185m		0	<1	
	Calcium	ppm	ASTM D5185m		28	24	
	Phosphorus	ppm		1650	2210	1954	
	Zinc	ppm	ASTM D5185m		22	48	
	Sulfur	ppm	ASTM D5185m		29329	25056	
	Visc @ 40°C	cSt	ASTM D445	143	190	187	













Sample No. Lab Number

Laboratory : LH0273222 : 06061552 Unique Number : 10832934 Test Package : CONST

: WearCheck USA - 501 Madison Ave., Cary, NC 27513 Recieved : 16 Jan 2024 Diagnosed : 17 Jan 2024 Diagnostician : Wes Davis

To discuss this sample report, contact Customer Service at 1-800-237-1369. * - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

RECO EQUIPMENT INC.

1040 REED DRIVE MONROE, OH US 45050

Contact: Eric Hansen ehansen@recoequip.com T: (513)539-5255

F: (513)539-5256