



WEAR	NORMAL
CONTAMINATION	NORMAL
FLUID CONDITION	NORMAL

Machine Id
CUMMINS MV JL BRADEN
Component
Port Genset
Fluid
CHEVRON DELO 710 LE (--- GAL)

RECOMMENDATION

Resample at the next service interval to monitor.

Test	UOM	Method	Limit/Abn	Current	History1	History2
Sample Number		Client Info		MW0038987	MW0038997	MW0056957
Sample Date		Client Info		09 Jan 2024	18 Oct 2023	23 Aug 2023
Machine Age	hrs	Client Info		8474	3057	2396
Oil Age	hrs	Client Info		0	0	0
Filter Age	hrs	Client Info		0	0	0
Oil Changed		Client Info		Changed	Changed	Changed
Filter Changed		Client Info		Changed	Changed	Changed
Sample Status				NORMAL	ABNORMAL	ABNORMAL

WEAR

All component wear rates are normal.

Iron	ppm	ASTM D5185m	>50	11	▲ 96	▲ 88
Chromium	ppm	ASTM D5185m	>4	1	3	2
Nickel	ppm	ASTM D5185m	>2	0	0	1
Titanium	ppm	ASTM D5185m		<1	<1	<1
Silver	ppm	ASTM D5185m	>5	0	0	<1
Aluminum	ppm	ASTM D5185m	>12	3	7	7
Lead	ppm	ASTM D5185m	>17	<1	▲ 54	▲ 45
Copper	ppm	ASTM D5185m	>70	<1	▲ 53	▲ 63
Tin	ppm	ASTM D5185m	>15	0	<1	<1
Vanadium	ppm	ASTM D5185m		<1	0	0
White Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE

CONTAMINATION







There is no indication of any contamination in the oil.

Silicon	ppm	ASTM D5185m	>25	6	18	18
Potassium	ppm	ASTM D5185m	>20	10	4	2
Fuel		WC Method	>4.0	<1.0	<1.0	<1.0
Water		WC Method	>0.1	NEG	NEG	NEG
Glycol		WC Method		NEG	NEG	NEG
Soot %	%	*ASTM D7844		0.1	0.3	0.3
Nitration	Abs/cm	*ASTM D7624	>20	12.5	17.5	16.9
Sulfation	Abs/.1mm	*ASTM D7415	>30	25.6	31.8	31.1
Silt	scalar	*Visual	NONE	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.1	NEG	NEG	NEG

FLUID CONDITION

The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

Sodium	ppm	ASTM D5185m		4	7	2
Boron	ppm	ASTM D5185m		252	151	167
Barium	ppm	ASTM D5185m		0	2	4
Molybdenum	ppm	ASTM D5185m		131	155	145
Manganese	ppm	ASTM D5185m		<1	8	9
Magnesium	ppm	ASTM D5185m		665	847	741
Calcium	ppm	ASTM D5185m		1663	1847	1720
Phosphorus	ppm	ASTM D5185m		700	774	710
Zinc	ppm	ASTM D5185m	10	846	1040	964
Sulfur	ppm	ASTM D5185m		2324	2436	2563
Oxidation	Abs/.1mm	*ASTM D7414	>25	27.7	42.4	39.5
Base Number (BN)	mg KOH/g	ASTM D2896	9.2	7.9	7.5	8.1
Visc @ 100°C	cSt	ASTM D445	15.5	12.5	16.4	15.7



Certificate L2367

Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513
Sample No. : MW0038987 **Recieved** : 16 Jan 2024
Lab Number : 06061654 **Diagnosed** : 17 Jan 2024
Unique Number : 10833036 **Diagnostician** : Don Baldrige
Test Package : MAR 2

To discuss this sample report, contact Customer Service at 1-800-237-1369.

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

C & B MARINE
 50 E RIVERCENTER BLVD, SUITE 1180
 COVINGTON, KY
 US 41011
 Contact: DAVID WESTRICH
 dwestrich@carlislebray.com
 T: (812)290-4063
 F: (859)655-7504