



WEAR	<b>NORMAL</b>
CONTAMINATION	<b>NORMAL</b>
FLUID CONDITION	<b>NORMAL</b>

Machine Id  
**929018-1272**  
 Component  
**Diesel Engine**  
 Fluid  
**PETRO CANADA DURON SHP 15W40 (--- GAL)**

**RECOMMENDATION**

Resample at the next service interval to monitor.

Test	UOM	Method	Limit/Abn	Current	History1	History2
Sample Number		Client Info		<b>GFL0103045</b>	GFL0102800	GFL0090462
Sample Date		Client Info		<b>11 Jan 2024</b>	30 Nov 2023	13 Oct 2023
Machine Age	hrs	Client Info		<b>11975</b>	11644	11368
Oil Age	hrs	Client Info		<b>607</b>	276	580
Filter Age	hrs	Client Info		<b>607</b>	276	580
Oil Changed		Client Info		<b>Changed</b>	Not Changd	Changed
Filter Changed		Client Info		<b>Changed</b>	Not Changd	Changed
Sample Status				<b>NORMAL</b>	NORMAL	NORMAL

**WEAR**

All component wear rates are normal.

Iron	ppm	ASTM D5185m	>100	<b>44</b>	4	11
Chromium	ppm	ASTM D5185m	>20	<b>3</b>	<1	2
Nickel	ppm	ASTM D5185m	>4	<b>0</b>	<1	<1
Titanium	ppm	ASTM D5185m		<b>0</b>	0	<1
Silver	ppm	ASTM D5185m	>3	<b>0</b>	0	0
Aluminum	ppm	ASTM D5185m	>20	<b>2</b>	2	3
Lead	ppm	ASTM D5185m	>40	<b>0</b>	<1	0
Copper	ppm	ASTM D5185m	>330	<b>1</b>	0	<1
Tin	ppm	ASTM D5185m	>15	<b>0</b>	<1	0
Vanadium	ppm	ASTM D5185m		<b>&lt;1</b>	0	0
White Metal	scalar	*Visual	NONE	<b>NONE</b>	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	<b>NONE</b>	NONE	NONE

**CONTAMINATION**







There is no indication of any contamination in the oil.

Silicon	ppm	ASTM D5185m	>25	<b>4</b>	2	2
Potassium	ppm	ASTM D5185m	>20	<b>3</b>	1	2
Fuel		WC Method	>5	<b>&lt;1.0</b>	<1.0	<1.0
Water		WC Method	>0.2	<b>NEG</b>	NEG	NEG
Glycol		WC Method		<b>NEG</b>	NEG	NEG
Soot %	%	*ASTM D7844	>3	<b>1</b>	0.4	0.6
Nitration	Abs/cm	*ASTM D7624	>20	<b>9.0</b>	5.9	7.0
Sulfation	Abs/.1mm	*ASTM D7415	>30	<b>20.9</b>	18.1	19.4
Silt	scalar	*Visual	NONE	<b>NONE</b>	NONE	NONE
Debris	scalar	*Visual	NONE	<b>NONE</b>	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	<b>NONE</b>	NONE	NONE
Appearance	scalar	*Visual	NORML	<b>NORML</b>	NORML	NORML
Odor	scalar	*Visual	NORML	<b>NORML</b>	NORML	NORML
Emulsified Water	scalar	*Visual	>0.2	<b>NEG</b>	NEG	NEG

**FLUID CONDITION**

The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

Sodium	ppm	ASTM D5185m		<b>4</b>	2	4
Boron	ppm	ASTM D5185m	0	<b>3</b>	6	2
Barium	ppm	ASTM D5185m	0	<b>0</b>	0	0
Molybdenum	ppm	ASTM D5185m	60	<b>62</b>	62	62
Manganese	ppm	ASTM D5185m	0	<b>&lt;1</b>	<1	0
Magnesium	ppm	ASTM D5185m	1010	<b>949</b>	920	927
Calcium	ppm	ASTM D5185m	1070	<b>1102</b>	1063	1054
Phosphorus	ppm	ASTM D5185m	1150	<b>1011</b>	1061	932
Zinc	ppm	ASTM D5185m	1270	<b>1240</b>	1283	1218
Sulfur	ppm	ASTM D5185m	2060	<b>2835</b>	3159	3348
Oxidation	Abs/.1mm	*ASTM D7414	>25	<b>15.8</b>	13.0	14.3
Base Number (BN)	mg KOH/g	ASTM D2896	9.8	<b>7.4</b>	8.2	8.4
Visc @ 100°C	cSt	ASTM D445	15.4	<b>13.7</b>	13.5	13.8



Certificate L2367

**Laboratory** : WearCheck USA - 501 Madison Ave., Cary, NC 27513  
**Sample No.** : GFL0103045 **Received** : 16 Jan 2024  
**Lab Number** : 06061689 **Diagnosed** : 17 Jan 2024  
**Unique Number** : 10833071 **Diagnostician** : Don Baldrige  
**Test Package** : FLEET

**GFL Environmental - 622 - Traverse City Hauling**  
 160 Hughes Dr  
 Traverse City, MI  
 US 49686  
 Contact: GARY BREWER

To discuss this sample report, contact Customer Service at 1-800-237-1369.  
 \* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.  
 Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

T:  
F: