



WEAR CHECK

OIL ANALYSIS REPORT

WEAR	ABNORMAL
CONTAMINATION	NORMAL
FLUID CONDITION	ATTENTION

Machine Id
2345
 Component
Diesel Engine
 Fluid
ROYAL PURPLE MOTOR OIL 15W40 (--- QTS)

RECOMMENDATION

Oil and filter change at the time of sampling has been noted. No corrective action is recommended at this time. Resample at the next service interval to monitor.

Test	UOM	Method	Limit/Abn	Current	History1	History2
Sample Number		Client Info		WC0720046	---	---
Sample Date		Client Info		10 Jan 2024	---	---
Machine Age	mls	Client Info		123517	---	---
Oil Age	mls	Client Info		100000	---	---
Filter Age	mls	Client Info		50000	---	---
Oil Changed		Client Info		Changed	---	---
Filter Changed		Client Info		Changed	---	---
Sample Status				ABNORMAL	---	---

WEAR

Cylinder, crank, or cam shaft wear is indicated. All other component wear rates are normal.

Iron	ppm	ASTM D5185m	>100	▲ 119	---	---
Chromium	ppm	ASTM D5185m	>20	4	---	---
Nickel	ppm	ASTM D5185m	>4	1	---	---
Titanium	ppm	ASTM D5185m		<1	---	---
Silver	ppm	ASTM D5185m	>3	0	---	---
Aluminum	ppm	ASTM D5185m	>20	30	---	---
Lead	ppm	ASTM D5185m	>40	2	---	---
Copper	ppm	ASTM D5185m	>330	143	---	---
Tin	ppm	ASTM D5185m	>15	4	---	---
Vanadium	ppm	ASTM D5185m		<1	---	---
White Metal	scalar	*Visual	NONE	NONE	---	---
Yellow Metal	scalar	*Visual	NONE	NONE	---	---

CONTAMINATION










Fuel content negligible. Elevated aluminum (Al) and/or lead (Pb) and potassium (K) levels in your metals analysis are likely a result of solder flux release into the lubricant and is common on new equipment/components.

Silicon	ppm	ASTM D5185m	>25	11	---	---
Potassium	ppm	ASTM D5185m	>20	76	---	---
Fuel	%	ASTM D3524	>5	0.3	---	---
Water		WC Method	>0.2	NEG	---	---
Glycol		WC Method		NEG	---	---
Soot %	%	*ASTM D7844	>3	1.4	---	---
Nitration	Abs/cm	*ASTM D7624	>20	14.9	---	---
Sulfation	Abs/.1mm	*ASTM D7415	>30	26.8	---	---
Silt	scalar	*Visual	NONE	NONE	---	---
Debris	scalar	*Visual	NONE	NONE	---	---
Sand/Dirt	scalar	*Visual	NONE	NONE	---	---
Appearance	scalar	*Visual	NORML	NORML	---	---
Odor	scalar	*Visual	NORML	NORML	---	---
Emulsified Water	scalar	*Visual	>0.2	NEG	---	---

FLUID CONDITION

The oil viscosity is lower than normal. The BN result indicates that there is suitable alkalinity remaining in the oil. Confirm oil type.

Sodium	ppm	ASTM D5185m		5	---	---
Boron	ppm	ASTM D5185m	0	4	---	---
Barium	ppm	ASTM D5185m	0	<1	---	---
Molybdenum	ppm	ASTM D5185m	100	58	---	---
Manganese	ppm	ASTM D5185m		3	---	---
Magnesium	ppm	ASTM D5185m	60	846	---	---
Calcium	ppm	ASTM D5185m	3050	1415	---	---
Phosphorus	ppm	ASTM D5185m	1050	886	---	---
Zinc	ppm	ASTM D5185m	1200	1184	---	---
Sulfur	ppm	ASTM D5185m	12500	2065	---	---
Oxidation	Abs/.1mm	*ASTM D7414	>25	29.4	---	---
Base Number (BN)	mg KOH/g	ASTM D2896	10.5	3.8	---	---
Visc @ 100°C	cSt	ASTM D445	14.9	▲ 12.4	---	---



Certificate L2367

Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513
Sample No. : WC0720046 **Received** : 16 Jan 2024
Lab Number : 06061865 **Diagnosed** : 18 Jan 2024
Unique Number : 10833247 **Diagnostician** : Don Baldrige
Test Package : FLEET (Additional Tests: FuelDilution, PercentFuel)

DILLON TRANSPORTATION
 974 TN WALTZ PARKWAY
 ASHLAND CITY, TN
 US 37015
 Contact: MASON NICHOLSON
 M.NICHOLSON@DILLONTRANSPORTATION.COM
 T: (615)792-5099
 F: (615)469-4200

To discuss this sample report, contact Customer Service at 1-800-237-1369.
 * - Denotes test methods that are outside of the ISO 17025 scope of accreditation.
 Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)