



WEAR	NORMAL
CONTAMINATION	NORMAL
FLUID CONDITION	NORMAL



Machine Id
JOHN DEERE 524K-II 1DW524KZKJF688574

Component
Hydraulic System

Fluid
JOHN DEERE HYDRAU (--- GAL)

RECOMMENDATION

Resample at the next service interval to monitor.

Test	UOM	Method	Limit/Abn	Current	History1	History2
Sample Number		Client Info		JR0201454	JR0185100	JR0176780
Sample Date		Client Info		09 Jan 2024	05 Oct 2023	28 Jun 2023
Machine Age	hrs	Client Info		9283	8699	8185
Oil Age	hrs	Client Info		1098	514	3639
Filter Age	hrs	Client Info		1098	514	3639
Oil Changed		Client Info		Not Changd	Not Changd	Changed
Filter Changed		Client Info		Not Changd	Not Changd	Changed
Sample Status				NORMAL	NORMAL	ABNORMAL

WEAR

All component wear rates are normal.

PQ		ASTM D8184	>50	16	16	12
Iron	ppm	ASTM D5185m	>71	4	4	10
Chromium	ppm	ASTM D5185m	>11	3	3	7
Nickel	ppm	ASTM D5185m	>6	0	<1	0
Titanium	ppm	ASTM D5185m		<1	0	<1
Silver	ppm	ASTM D5185m		0	0	0
Aluminum	ppm	ASTM D5185m	>11	2	0	3
Lead	ppm	ASTM D5185m	>13	0	<1	0
Copper	ppm	ASTM D5185m	>21	2	1	2
Tin	ppm	ASTM D5185m	>5	<1	0	0
Vanadium	ppm	ASTM D5185m		0	0	<1
White Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE

CONTAMINATION












The system cleanliness is acceptable for your target ISO 4406 cleanliness code. The system and fluid cleanliness is acceptable.

Silicon	ppm	ASTM D5185m	>24	1	1	2
Potassium	ppm	ASTM D5185m	>20	1	<1	<1
Water		WC Method	>0.075	NEG	NEG	NEG
Particles >4µm		ASTM D7647	>80000	1886	2777	---
Particles >6µm		ASTM D7647	>5000	458	672	---
Particles >14µm		ASTM D7647	>640	32	71	---
Particles >21µm		ASTM D7647	>160	9	20	---
Particles >38µm		ASTM D7647	>40	1	2	---
Particles >71µm		ASTM D7647	>10	1	0	---
Oil Cleanliness		ISO 4406 (c)	>23/19/16	18/16/12	19/17/13	---
Silt	scalar	*Visual	NONE	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE	▲ MODER
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.075	NEG	NEG	NEG

FLUID CONDITION

The AN level is acceptable for this fluid. The condition of the oil is suitable for further service.

Sodium	ppm	ASTM D5185m	>21	0	<1	3
Boron	ppm	ASTM D5185m		0	0	0
Barium	ppm	ASTM D5185m		0	0	0
Molybdenum	ppm	ASTM D5185m		<1	<1	<1
Manganese	ppm	ASTM D5185m		0	0	<1
Magnesium	ppm	ASTM D5185m		0	4	2
Calcium	ppm	ASTM D5185m	87	102	99	93
Phosphorus	ppm	ASTM D5185m	727	608	619	626
Zinc	ppm	ASTM D5185m	900	815	831	810
Sulfur	ppm	ASTM D5185m	1500	1565	1780	1862
Acid Number (AN)	mg KOH/g	ASTM D8045	1.0	0.63	0.60	0.50
Visc @ 40°C	cSt	ASTM D445	65	59.7	59.5	58.7



Certificate L2367

Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513
Sample No. : JR0201454 **Received** : 16 Jan 2024
Lab Number : 06061896 **Diagnosed** : 17 Jan 2024
Unique Number : 10833278 **Diagnostician** : Wes Davis
Test Package : CONST (Additional Tests: PQ)

To discuss this sample report, contact Customer Service at 1-800-237-1369.

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

JRE - ASHEVILLE
 101 BRUCE DRIVE
 ASHEVILLE, NC
 US 28806

Contact: Randy Warren
 randy.warren@jamesriverequipment.com

T: (528)667-0176
 F: (828)667-4865