



|                 |               |
|-----------------|---------------|
| WEAR            | <b>NORMAL</b> |
| CONTAMINATION   | <b>NORMAL</b> |
| FLUID CONDITION | <b>NORMAL</b> |

Machine Id  
**920094-260373**

Component  
**Transmission**

Fluid  
**PETRO CANADA DuraDrive HD Synthetic 668 (--- GAL)**

**RECOMMENDATION**

Resample at the next service interval to monitor.

| Test           | UOM | Method      | Limit/Abn | Current            | History1 | History2 |
|----------------|-----|-------------|-----------|--------------------|----------|----------|
| Sample Number  |     | Client Info |           | <b>GFL0102461</b>  | ---      | ---      |
| Sample Date    |     | Client Info |           | <b>06 Jan 2024</b> | ---      | ---      |
| Machine Age    | hrs | Client Info |           | <b>9080</b>        | ---      | ---      |
| Oil Age        | hrs | Client Info |           | <b>0</b>           | ---      | ---      |
| Filter Age     | hrs | Client Info |           | <b>0</b>           | ---      | ---      |
| Oil Changed    |     | Client Info |           | <b>Changed</b>     | ---      | ---      |
| Filter Changed |     | Client Info |           | <b>Changed</b>     | ---      | ---      |
| Sample Status  |     |             |           | <b>NORMAL</b>      | ---      | ---      |

**WEAR**

All component wear rates are normal.

|              |        |             |      |             |     |     |
|--------------|--------|-------------|------|-------------|-----|-----|
| Iron         | ppm    | ASTM D5185m | >200 | <b>24</b>   | --- | --- |
| Chromium     | ppm    | ASTM D5185m | >10  | <b>0</b>    | --- | --- |
| Nickel       | ppm    | ASTM D5185m |      | <b>0</b>    | --- | --- |
| Titanium     | ppm    | ASTM D5185m |      | <b>0</b>    | --- | --- |
| Silver       | ppm    | ASTM D5185m |      | <b>0</b>    | --- | --- |
| Aluminum     | ppm    | ASTM D5185m | >50  | <b>17</b>   | --- | --- |
| Lead         | ppm    | ASTM D5185m | >50  | <b>5</b>    | --- | --- |
| Copper       | ppm    | ASTM D5185m | >200 | <b>10</b>   | --- | --- |
| Tin          | ppm    | ASTM D5185m | >10  | <b>3</b>    | --- | --- |
| Vanadium     | ppm    | ASTM D5185m |      | <b>0</b>    | --- | --- |
| White Metal  | scalar | *Visual     | NONE | <b>NONE</b> | --- | --- |
| Yellow Metal | scalar | *Visual     | NONE | <b>NONE</b> | --- | --- |

**CONTAMINATION**





There is no indication of any contamination in the fluid.

|                  |        |             |       |              |     |     |
|------------------|--------|-------------|-------|--------------|-----|-----|
| Silicon          | ppm    | ASTM D5185m | >50   | <b>5</b>     | --- | --- |
| Potassium        | ppm    | ASTM D5185m | >20   | <b>0</b>     | --- | --- |
| Water            |        | WC Method   | >0.1  | <b>NEG</b>   | --- | --- |
| Silt             | scalar | *Visual     | NONE  | <b>NONE</b>  | --- | --- |
| Debris           | scalar | *Visual     | NONE  | <b>NONE</b>  | --- | --- |
| Sand/Dirt        | scalar | *Visual     | NONE  | <b>NONE</b>  | --- | --- |
| Appearance       | scalar | *Visual     | NORML | <b>NORML</b> | --- | --- |
| Odor             | scalar | *Visual     | NORML | <b>NORML</b> | --- | --- |
| Emulsified Water | scalar | *Visual     | >0.1  | <b>NEG</b>   | --- | --- |

**FLUID CONDITION**

The condition of the fluid is acceptable for the time in service.

|             |     |             |    |             |     |     |
|-------------|-----|-------------|----|-------------|-----|-----|
| Sodium      | ppm | ASTM D5185m |    | <b>3</b>    | --- | --- |
| Boron       | ppm | ASTM D5185m |    | <b>59</b>   | --- | --- |
| Barium      | ppm | ASTM D5185m |    | <b>0</b>    | --- | --- |
| Molybdenum  | ppm | ASTM D5185m |    | <b>0</b>    | --- | --- |
| Manganese   | ppm | ASTM D5185m |    | <b>1</b>    | --- | --- |
| Magnesium   | ppm | ASTM D5185m |    | <b>2</b>    | --- | --- |
| Calcium     | ppm | ASTM D5185m |    | <b>118</b>  | --- | --- |
| Phosphorus  | ppm | ASTM D5185m |    | <b>202</b>  | --- | --- |
| Zinc        | ppm | ASTM D5185m |    | <b>10</b>   | --- | --- |
| Sulfur      | ppm | ASTM D5185m |    | <b>1956</b> | --- | --- |
| Visc @ 40°C | cSt | ASTM D445   | 34 | <b>33.2</b> | --- | --- |



Certificate L2367

**Laboratory** : WearCheck USA - 501 Madison Ave., Cary, NC 27513  
**Sample No.** : GFL0102461 **Received** : 16 Jan 2024  
**Lab Number** : **06062265** **Diagnosed** : 18 Jan 2024  
**Unique Number** : 10833647 **Diagnostician** : Wes Davis  
**Test Package** : FLEET

**GFL Environmental - 820 - Joplin Hauling**  
 3700 West 7th Street  
 Joplin, MO  
 US 64801  
 Contact: James Jarrett  
 jjarrett@gflenv.com  
 T: (417)310-2802  
 F:

To discuss this sample report, contact Customer Service at 1-800-237-1369.

\* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)