



VOLVO

OIL ANALYSIS REPORT

WEAR	NORMAL
CONTAMINATION	NORMAL
FLUID CONDITION	NORMAL



Area
[634802]
Machine Id
VOLVO A30G 752326
Component
Diesel Engine
Fluid
VOLVO ULTRA DIESEL ENGINE OIL 15W40 VDS-3 (--- GAL)

RECOMMENDATION

No corrective action is recommended at this time. Resample at the next service interval to monitor.

Test	UOM	Method	Limit/Abn	Current	History1	History2
Sample Number		Client Info		VCP432194	VCP425841	VCP393522
Sample Date		Client Info		30 Nov 2023	06 Jun 2023	08 Mar 2023
Machine Age	hrs	Client Info		4560	5591	3043
Oil Age	hrs	Client Info		500	0	500
Filter Age	hrs	Client Info		0	0	0
Oil Changed		Client Info		Changed	Changed	Changed
Filter Changed		Client Info		Changed	Changed	Changed
Sample Status				NORMAL	SEVERE	MARGINAL

WEAR

All component wear rates are normal.

Iron	ppm	ASTM D5185m	>200	7	0	8
Chromium	ppm	ASTM D5185m	>20	<1	0	<1
Nickel	ppm	ASTM D5185m	>10	<1	0	<1
Titanium	ppm	ASTM D5185m		0	6	<1
Silver	ppm	ASTM D5185m	>2	0	0	0
Aluminum	ppm	ASTM D5185m	>30	3	6	2
Lead	ppm	ASTM D5185m	>40	<1	0	<1
Copper	ppm	ASTM D5185m	>20	6	0	2
Tin	ppm	ASTM D5185m	>20	<1	0	<1
Vanadium	ppm	ASTM D5185m		<1	0	<1
White Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE

CONTAMINATION












Fuel content negligible. There is no indication of any contamination in the oil.

Silicon	ppm	ASTM D5185m	>20	4	2	2
Potassium	ppm	ASTM D5185m	>20	0	2	2
Fuel	%	ASTM D3524	>3.0	0.4	6.5	0.4
Water		WC Method	>0.2	NEG	NEG	NEG
Glycol		WC Method		NEG	NEG	NEG
Soot %	%	*ASTM D7844	>3	0.4	0.3	0.4
Nitration	Abs/cm	*ASTM D7624	>20	8.0	7.8	8.3
Sulfation	Abs/.1mm	*ASTM D7415	>30	21.4	20.8	22.1
Silt	scalar	*Visual	NONE	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.2	NEG	NEG	NEG

FLUID CONDITION

The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

Sodium	ppm	ASTM D5185m		2	2	0
Boron	ppm	ASTM D5185m	2.5	28	49	28
Barium	ppm	ASTM D5185m	0.0	0	12	2
Molybdenum	ppm	ASTM D5185m	0.7	44	46	73
Manganese	ppm	ASTM D5185m	0.0	<1	0	<1
Magnesium	ppm	ASTM D5185m	256	512	513	457
Calcium	ppm	ASTM D5185m	2057	1796	1949	1764
Phosphorus	ppm	ASTM D5185m	935	995	1052	946
Zinc	ppm	ASTM D5185m	1223	1170	1271	1151
Sulfur	ppm	ASTM D5185m	4079	3126	3823	2715
Oxidation	Abs/.1mm	*ASTM D7414	>25	19.6	18.0	19.6
Base Number (BN)	mg KOH/g	ASTM D2896	10	9.8	9.4	8.7
Visc @ 100°C	cSt	ASTM D445	15.0	12.8	10.7	12.4



Certificate L2367

Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513
Sample No. : VCP432194 **Received** : 17 Jan 2024
Lab Number : 06062324 **Diagnosed** : 19 Jan 2024
Unique Number : 10833706 **Diagnostician** : Wes Davis
Test Package : MOB 1 (Additional Tests: PercentFuel, TBN)

To discuss this sample report, contact Customer Service at 1-800-237-1369.

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

RIPA AND ASSOCIATES
 10149 FISHER AVENUE
 TAMPA, FL
 US 33619

Contact: PM Services
 PMServices@ripaconstruction.com

T:
F: