



OIL ANALYSIS REPORT

WEAR	NORMAL
CONTAMINATION	NORMAL
FLUID CONDITION	NORMAL

Area

Off Road

Machine Id

HAMM HD12 RA120 (S/N H2004063)

Component

Diesel Engine

Fluid

CASTROL HYPURON ADVANCED FORMULA (--- GAL)

RECOMMENDATION

Resample at the next service interval to monitor.

Test	UOM	Method	Limit/Abn	Current	History1	History2
Sample Number		Client Info		WC0675099	WC0314391	WCMCF49339
Sample Date		Client Info		11 Dec 2023	04 Mar 2019	15 Jan 2018
Machine Age	hrs	Client Info		2481	1373	1058
Oil Age	hrs	Client Info		45	300	300
Filter Age	hrs	Client Info		45	300	300
Oil Changed		Client Info		Changed	Changed	Changed
Filter Changed		Client Info		Changed	Changed	Changed
Sample Status				NORMAL	NORMAL	NORMAL

WEAR

All component wear rates are normal.

Iron	ppm	ASTM D5185m	>100	2	9	7
Chromium	ppm	ASTM D5185m	>20	0	<1	<1
Nickel	ppm	ASTM D5185m	>4	0	0	0
Titanium	ppm	ASTM D5185m		0	0	0
Silver	ppm	ASTM D5185m	>3	0	0	0
Aluminum	ppm	ASTM D5185m	>20	<1	2	3
Lead	ppm	ASTM D5185m	>40	0	<1	0
Copper	ppm	ASTM D5185m	>330	<1	1	<1
Tin	ppm	ASTM D5185m	>15	0	0	0
Vanadium	ppm	ASTM D5185m		<1	0	0
White Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE

CONTAMINATION







There is no indication of any contamination in the oil.

Silicon	ppm	ASTM D5185m	>25	7	8	11
Potassium	ppm	ASTM D5185m	>20	<1	2	<1
Fuel		WC Method	>5	<1.0	<1.0	<1.0
Water		WC Method	>0.2	NEG	NEG	NEG
Glycol		WC Method		NEG	NEG	NEG
Soot %	%	*ASTM D7844	>3	0.1	0.1	0
Nitration	Abs/cm	*ASTM D7624	>20	4.7	6.7	6.
Sulfation	Abs/.1mm	*ASTM D7415	>30	16.8	18.2	16.
Silt	scalar	*Visual	NONE	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.2	NEG	NEG	NEG

FLUID CONDITION

The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

Sodium	ppm	ASTM D5185m		<1	6	19
Boron	ppm	ASTM D5185m		6	54	71
Barium	ppm	ASTM D5185m		0	0	0
Molybdenum	ppm	ASTM D5185m		53	48	47
Manganese	ppm	ASTM D5185m		0	<1	<1
Magnesium	ppm	ASTM D5185m		897	1000	704
Calcium	ppm	ASTM D5185m		1132	1243	1326
Phosphorus	ppm	ASTM D5185m		980	1007	984
Zinc	ppm	ASTM D5185m		1234	1277	1081
Sulfur	ppm	ASTM D5185m		3291	3209	3836
Oxidation	Abs/.1mm	*ASTM D7414	>25	12.0	14.7	12.
Base Number (BN)	mg KOH/g	ASTM D2896	10.6	9.4	9	8.57
Visc @ 100°C	cSt	ASTM D445	12.1	11.2	10.99	10.79



Certificate L2367

Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513
Sample No. : WC0675099 **Received** : 17 Jan 2024
Lab Number : 06062437 **Diagnosed** : 18 Jan 2024
Unique Number : 10833819 **Diagnostician** : Wes Davis
Test Package : CONST (Additional Tests: TBN)

To discuss this sample report, contact Customer Service at 1-800-237-1369.

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

GRAY & SON INC
 430 W PADONIA RD
 TIMONIUM, MD
 US 21093-2274
 Contact: DON WIMER
 dwimer@graynson.com
 T: (410)771-4311
 F: (410)560-0394