



WEAR	NORMAL
CONTAMINATION	NORMAL
FLUID CONDITION	NORMAL



Machine Id
JOHN DEERE 650J 9X1 (S/N T0650VX127477)
Component
Diesel Engine
Fluid
JD TORQUE GUARD 10W30 (15 QTS)

RECOMMENDATION

Resample at the next service interval to monitor.

Test	UOM	Method	Limit/Abn	Current	History1	History2
Sample Number		Client Info		JR0191254	JR0149503	JR0111808
Sample Date		Client Info		21 Dec 2023	17 Nov 2022	18 Nov 2021
Machine Age	hrs	Client Info		1510	1437	1347
Oil Age	hrs	Client Info		152	1357	83
Filter Age	hrs	Client Info		152	1357	83
Oil Changed		Client Info		Not Changd	Not Changd	Not Changd
Filter Changed		Client Info		Not Changd	Not Changd	Not Changd
Sample Status				NORMAL	NORMAL	NORMAL

WEAR

All component wear rates are normal.

Iron	ppm	ASTM D5185m	>51	10	5	6
Chromium	ppm	ASTM D5185m	>11	<1	<1	<1
Nickel	ppm	ASTM D5185m	>5	<1	0	0
Titanium	ppm	ASTM D5185m		0	0	<1
Silver	ppm	ASTM D5185m	>3	0	0	0
Aluminum	ppm	ASTM D5185m	>31	1	<1	3
Lead	ppm	ASTM D5185m	>26	<1	<1	<1
Copper	ppm	ASTM D5185m	>26	<1	<1	<1
Tin	ppm	ASTM D5185m	>4	<1	0	<1
Vanadium	ppm	ASTM D5185m		<1	0	0
White Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE

CONTAMINATION







There is no indication of any contamination in the oil.

Silicon	ppm	ASTM D5185m	>22	4	3	4
Potassium	ppm	ASTM D5185m	>20	<1	2	0
Fuel		WC Method	>2.1	<1.0	<1.0	<1.0
Water		WC Method	>0.21	NEG	NEG	NEG
Glycol		WC Method		NEG	NEG	NEG
Soot %	%	*ASTM D7844	>3	0.2	0.1	0.2
Nitration	Abs/cm	*ASTM D7624	>20	6.8	6.4	7.7
Sulfation	Abs/.1mm	*ASTM D7415	>30	15.5	15.6	19.3
Silt	scalar	*Visual	NONE	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.21	NEG	NEG	NEG

FLUID CONDITION

The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

Sodium	ppm	ASTM D5185m	>31	0	0	1
Boron	ppm	ASTM D5185m		8	8	83
Barium	ppm	ASTM D5185m		0	0	0
Molybdenum	ppm	ASTM D5185m		3	2	2
Manganese	ppm	ASTM D5185m		<1	<1	<1
Magnesium	ppm	ASTM D5185m		287	284	744
Calcium	ppm	ASTM D5185m		2140	2240	1312
Phosphorus	ppm	ASTM D5185m		1046	1095	1110
Zinc	ppm	ASTM D5185m		1315	1283	1186
Sulfur	ppm	ASTM D5185m		3471	4238	3442
Oxidation	Abs/.1mm	*ASTM D7414	>25	10.9	10.6	13.3
Base Number (BN)	mg KOH/g	ASTM D2896		9.1	10.5	8.9
Visc @ 100°C	cSt	ASTM D445		10.6	10.6	11.1



Certificate L2367

Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513
Sample No. : JR0191254 **Received** : 17 Jan 2024
Lab Number : 06062476 **Diagnosed** : 18 Jan 2024
Unique Number : 10833858 **Diagnostician** : Wes Davis
Test Package : CONST (Additional Tests: TBN)

NORTH CAROLINA FOREST SERVICE
 133 Glenn Cave Road
 SYLVA, NC
 US 28779
 Contact: GEOFF BRATLAND
 GEOFF.BRATLAND@NCAGR.GOV
 T: (828)586-4007
 F: (828)586-4008

To discuss this sample report, contact Customer Service at 1-800-237-1369.

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)