WEAR CONTAMINATION FLUID CONDITION

NORMAL NORMAL NORMAL

JOHN DEERE 2032R 1LV2032RALL119335

Component Diesel Engine

RECOMMENDATION	Test	UOM	Method	Limit/Abn	Current	History1	History
Resample at the next service interval to monitor.	Sample Number		Client Info		JR0193215		
	Sample Date		Client Info		11 Jan 2024		
	Machine Age	hrs	Client Info		121		
	Oil Age	hrs	Client Info		0		
	Filter Age	hrs	Client Info		0		
	Oil Changed		Client Info		N/A		
	Filter Changed		Client Info		N/A		
	Sample Status				NORMAL		
VEAR	Iron	nnm	ASTM D5185m	<u> </u>	10		
WLAN	Chromium	ppm	ASTM D5185m		0		
Metal levels are typical for a new component breaking in.	Nickel	ppm	ASTM D5185m		0		
	Titanium	ppm	ASTM D5185m	>5	0		
		ppm		. 0	-		
	Silver	ppm	ASTM D5185m		0		
	Aluminum	ppm	ASTM D5185m		4		
	Lead	ppm	ASTM D5185m		2		
	Copper	ppm	ASTM D5185m		4		
	Tin	ppm	ASTM D5185m	>4	0		
	Vanadium	ppm	ASTM D5185m	NONE	<1 NONE		
	White Metal	scalar	*Visual	NONE	NONE		
	Yellow Metal	scalar	*Visual	NONE	NONE		
ONTAMINATION	Silicon	ppm	ASTM D5185m	>22	14		
There is no indication of any contamination in the oil.	Potassium	ppm	ASTM D5185m	>20	1		
	Fuel		WC Method	>2.1	<1.0		
	Water		WC Method	>0.21	NEG		
	Glycol		WC Method		NEG		
	Soot %	%	*ASTM D7844	>3	0.1		
	Nitration	Abs/cm	*ASTM D7624	>20	6.8		
	Sulfation	Abs/.1mm	*ASTM D7415	>30	19.5		
	Silt	scalar	*Visual	NONE	NONE		
	Debris	scalar	*Visual	NONE	NONE		
	Sand/Dirt	scalar	*Visual	NONE	NONE		
	Appearance	scalar	*Visual	NORML	NORML		
	Odor	scalar	*Visual	NORML	NORML		
	Emulsified Water	scalar	*Visual	>0.21	NEG		
LUB CONDITION							
LUID CONDITION	Sodium	ppm	ASTM D5185m	>31	2		
The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.	Boron	ppm	ASTM D5185m		235		
	Barium	ppm	ASTM D5185m		0		
	Molybdenum	ppm	ASTM D5185m		231		
	Manganese	ppm	ASTM D5185m		<1		
	Magnesium	ppm	ASTM D5185m		839		
	Calcium	ppm	ASTM D5185m		1459		
	Phosphorus	ppm	ASTM D5185m		869		
	Zinc	ppm	ASTM D5185m		1051		
	Sulfur	ppm	ASTM D5185m		3007		
		Abs/.1mm	*ASTM D7414	>25	14.7		
	Oxidation						
	Oxidation Base Number (BN)				9.7		







Unique Number

Laboratory Sample No. Lab Number

: JR0193215 : 06062480 : 10833862

: WearCheck USA - 501 Madison Ave., Cary, NC 27513 Recieved Diagnosed

: 18 Jan 2024

Diagnostician : Wes Davis

: 17 Jan 2024

Test Package : CONST (Additional Tests: TBN) To discuss this sample report, contact Customer Service at 1-800-237-1369.

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation. Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

JRE - STATESVILLE 635 MOCKSVILLE HWY

STATESVILLE, NC US 28625

Contact: MIKE CRANFILL MCRANFILL@JAMESRIVEREQUIPMENT.COM

T: (704)872-6411