
**WEAR** CONTAMINATION **FLUID CONDITION**  **NORMAL NORMAL NORMAL** 

**OIL ANALYSIS REPORT** 

Machine Id **WEILER 0033** 

Component Left Final Drive Fluid

RECOMMENDATION	Test	UOM	Method	Limit/Abn	Current	History1	History2
	Sample Number	OOW	Client Info	LIIIIUADII	TR06062952	_	
Resample at the next service interval to monitor.	Sample Date		Client Info		08 Nov 2023	04 Jun 2020	
	Machine Age	hrs	Client Info		400	64	
	Oil Age	hrs	Client Info		196	64	
	Filter Age	hrs	Client Info		0	64	
	Oil Changed		Client Info		Changed	Changed	
	Filter Changed		Client Info		Not Changd	Changed	
	Sample Status				NORMAL	NORMAL	
WEAR	Iron	ppm	ASTM D5185m	>500	64	69	
All component wear rates are normal.	Chromium	ppm	ASTM D5185m	>10	1	3	
	Nickel	ppm	ASTM D5185m	>10	0	0	
	Titanium	ppm	ASTM D5185m		<1	<1	
	Silver	ppm	ASTM D5185m		0	0	
	Aluminum	ppm	ASTM D5185m	>25	0	<1	
	Lead	ppm	ASTM D5185m	>25	0	0	
	Copper	ppm	ASTM D5185m	>50	15	11	
	Tin	ppm	ASTM D5185m	>10	0	0	
	Vanadium	ppm	ASTM D5185m		<1	0	
	White Metal	scalar	*Visual	NONE	NONE	LIGHT	
	Yellow Metal	scalar	*Visual	NONE	NONE	NONE	
CONTAMINATION	Silicon	nnm	ASTM D5185m	<u>~75</u>	4	5	
CONTAININATION	Potassium	ppm	ASTM D5185m		2	8	
There is no indication of any contamination in the oil.	Water	ррпп	WC Method	>0.2	NEG	NEG	
	Silt	scalar	*Visual	NONE	NONE	NONE	
	Debris	scalar	*Visual	NONE	NONE	LIGHT	
	Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	
	Appearance	scalar	*Visual	NORML	NORML	NORML	
	Odor	scalar	*Visual	NORML	NORML	NORML	
	Emulsified Water	scalar	*Visual	>0.2	NEG	NEG	
FLUID CONDITION	Sodium	ppm	ASTM D5185m		<1	2	
The AN level is acceptable for this fluid. The condition of the oil is	Boron	ppm	ASTM D5185m		9	22	
suitable for further service.	Barium	ppm	ASTM D5185m		0	0	
	Molybdenum	ppm	ASTM D5185m		<1	2	
	Manganese	ppm	ASTM D5185m		2	4	
	Magnesium	ppm	ASTM D5185m		0	4	
	Calcium	ppm	ASTM D5185m		136	34	
	Phosphorus	ppm	ASTM D5185m	1000	686	435	
	Zinc	ppm	ASTM D5185m		39	28	
	Sulfur	ppm	ASTM D5185m	17000	17477	19304	
	Acid Number (AN)	0 0	ASTM D8045		1.03	1.077	
	Visc @ 40°C	cSt	ASTM D445		152		
	Visc @ 100°C	cSt	ASTM D445	18	16.1	20.1	
	Viscosity Index (VI)		ASTM D2270		110		





Certificate L2367

Laboratory Sample No. Lab Number **Unique Number** 

: 06062952

: TR06062952 : 10834334

: WearCheck USA - 501 Madison Ave., Cary, NC 27513 Recieved : 17 Jan 2024

Diagnosed : 19 Jan 2024 Diagnostician : Don Baldridge

Test Package : MOB 2 ( Additional Tests: KV100, VI )

To discuss this sample report, contact Customer Service at 1-800-827-0711. \* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

RANDALL COUNTY ROAD DEPT.

301 WEST HIGHWAY 60 CANYON, TX US 79015

Contact: MIKE LEWIS

T: F: