



TRAAP

Texas Refinery Advanced Analysis Program

OIL ANALYSIS REPORT

WEAR	NORMAL
CONTAMINATION	NORMAL
FLUID CONDITION	NORMAL

Machine Id
MACK 1035

Component
Diesel Engine

Fluid
TRC PRO-SPEC III SYNTHETIC BLEND 15W40 (10 GAL)

RECOMMENDATION

Resample at the next service interval to monitor.

Test	UOM	Method	Limit/Abn	Current	History1	History2
Sample Number		Client Info		TR06062974	TR05829129	TR05349416
Sample Date		Client Info		06 Dec 2023	22 Mar 2023	12 Jul 2021
Machine Age	mls	Client Info		84321	74841	51000
Oil Age	mls	Client Info		9480	10208	9960
Filter Age	mls	Client Info		9480	10208	9960
Oil Changed		Client Info		Changed	Changed	Changed
Filter Changed		Client Info		Changed	Changed	Changed
Sample Status				NORMAL	NORMAL	NORMAL

WEAR

All component wear rates are normal.

Iron	ppm	ASTM D5185m	>120	12	12	15
Chromium	ppm	ASTM D5185m	>20	<1	0	<1
Nickel	ppm	ASTM D5185m	>5	0	0	<1
Titanium	ppm	ASTM D5185m	>2	0	0	<1
Silver	ppm	ASTM D5185m	>2	0	0	<1
Aluminum	ppm	ASTM D5185m	>20	4	4	6
Lead	ppm	ASTM D5185m	>40	<1	0	2
Copper	ppm	ASTM D5185m	>330	7	3	14
Tin	ppm	ASTM D5185m	>15	<1	<1	2
Vanadium	ppm	ASTM D5185m		<1	0	<1
White Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE

CONTAMINATION











There is no indication of any contamination in the oil.

Silicon	ppm	ASTM D5185m	>25	5	4	5
Potassium	ppm	ASTM D5185m	>20	5	2	15
Fuel		WC Method	>3.0	<1.0	<1.0	<1.0
Water		WC Method	>0.2	NEG	NEG	NEG
Glycol		WC Method		NEG	NEG	NEG
Soot %	%	*ASTM D7844	>4	0.3	0.2	0.3
Nitration	Abs/cm	*ASTM D7624	>20	7.4	7.2	8.2
Sulfation	Abs/.1mm	*ASTM D7415	>30	19.5	18.5	21.1
Silt	scalar	*Visual	NONE	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.2	NEG	NEG	NEG

FLUID CONDITION

The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

Sodium	ppm	ASTM D5185m		3	3	1
Boron	ppm	ASTM D5185m		0	0	0
Barium	ppm	ASTM D5185m		0	0	0
Molybdenum	ppm	ASTM D5185m		<1	<1	<1
Manganese	ppm	ASTM D5185m		<1	<1	<1
Magnesium	ppm	ASTM D5185m		5	27	17
Calcium	ppm	ASTM D5185m		4911	4641	4542
Phosphorus	ppm	ASTM D5185m		892	898	1033
Zinc	ppm	ASTM D5185m		1165	1115	1250
Sulfur	ppm	ASTM D5185m		3932	4513	4378
Oxidation	Abs/.1mm	*ASTM D7414	>25	11.4	10.6	14.6
Base Number (BN)	mg KOH/g	ASTM D2896		13.24	14.31	13.1
Visc @ 100°C	cSt	ASTM D445	15.5	14.0	13.7	14.6



Certificate L2367

Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513
Sample No. : TR06062974 **Recieved** : 17 Jan 2024
Lab Number : 06062974 **Diagnosed** : 18 Jan 2024
Unique Number : 10834356 **Diagnostician** : Sean Felton
Test Package : MOB 2

RANDALL COUNTY ROAD DEPT.
 301 WEST HIGHWAY 60
 CANYON, TX
 US 79015
 Contact: MIKE LEWIS

To discuss this sample report, contact Customer Service at 1-800-827-0711.

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

T:
F: