WEAR CONTAMINATION FLUID CONDITION **NORMAL NORMAL NORMAL**

JOHN DEERE 2032R 1LV2032RALL119335

Component
Transmission (Manual)
Fluid

| RECOMMENDATION | Test | UOM | Method | Limit/Abn | Current | History1 | History2 |
|---|------------------|--------|-------------|-----------|-------------|----------|----------|
| Resample at the next service interval to monitor. | Sample Number | | Client Info | | JR0193207 | | |
| | Sample Date | | Client Info | | 11 Jan 2024 | | |
| | Machine Age | hrs | Client Info | | 121 | | |
| | Oil Age | hrs | Client Info | | 0 | | |
| | Filter Age | hrs | Client Info | | 0 | | |
| | Oil Changed | | Client Info | | N/A | | |
| | Filter Changed | | Client Info | | N/A | | |
| | Sample Status | | | | NORMAL | | |
| WEAR | PQ | | ASTM D8184 | >95 | 21 | | |
| All component wear rates are normal. | Iron | ppm | ASTM D5185m | >200 | 24 | | |
| All component wear rates are normal. | Chromium | ppm | ASTM D5185m | >5 | <1 | | |
| | Nickel | ppm | ASTM D5185m | >5 | 0 | | |
| | Titanium | ppm | ASTM D5185m | | 0 | | |
| | Silver | ppm | ASTM D5185m | >7 | 2 | | |
| | Aluminum | ppm | ASTM D5185m | | 3 | | |
| | Lead | ppm | ASTM D5185m | | 2 | | |
| | Copper | ppm | ASTM D5185m | | 48 | | |
| | Tin | ppm | ASTM D5185m | >10 | <1 | | |
| | Vanadium | ppm | ASTM D5185m | NONE | <1 NOVE | | |
| | White Metal | scalar | *Visual | NONE | NONE | | |
| | Yellow Metal | scalar | *Visual | NONE | NONE | | |
| CONTAMINATION | Silicon | ppm | ASTM D5185m | >125 | 11 | | |
| There is no indication of any contamination in the fluid. | Potassium | ppm | ASTM D5185m | >20 | 1 | | |
| | Water | | WC Method | >0.1 | NEG | | |
| | Silt | scalar | *Visual | NONE | NONE | | |
| | Debris | scalar | *Visual | NONE | NONE | | |
| | Sand/Dirt | scalar | *Visual | NONE | NONE | | |
| | Appearance | scalar | *Visual | NORML | NORML | | |
| | Odor | scalar | *Visual | NORML | NORML | | |
| | Emulsified Water | scalar | *Visual | >0.1 | NEG | | |
| FLUID CONDITION | Sodium | ppm | ASTM D5185m | | 3 | | |
| The condition of the fluid is acceptable for the time in service. | Boron | ppm | ASTM D5185m | 6 | 3 | | |
| | Barium | ppm | ASTM D5185m | 0 | 0 | | |
| | Molybdenum | ppm | ASTM D5185m | 0 | 0 | | |
| | Manganese | ppm | ASTM D5185m | | 2 | | |
| | Magnesium | ppm | ASTM D5185m | | 85 | | |
| | Calcium | ppm | ASTM D5185m | | 3345 | | |
| | Phosphorus | ppm | ASTM D5185m | | 874 | | |
| | Zinc | ppm | ASTM D5185m | 1640 | 1192 | | |
| | Sulfur | ppm | ASTM D5185m | | 3279 | | |





Laboratory Sample No. Lab Number **Unique Number**

: JR0193207 : 06062991 : 10834373

: WearCheck USA - 501 Madison Ave., Cary, NC 27513 Recieved : 17 Jan 2024 Diagnosed

: 18 Jan 2024 Diagnostician : Sean Felton Test Package : CONST (Additional Tests: PQ)

JRE - STATESVILLE 635 MOCKSVILLE HWY STATESVILLE, NC US 28625

Contact: MIKE CRANFILL MCRANFILL@JAMESRIVEREQUIPMENT.COM T: (704)872-6411

To discuss this sample report, contact Customer Service at 1-800-237-1369. * - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)