



|                 |               |
|-----------------|---------------|
| WEAR            | <b>NORMAL</b> |
| CONTAMINATION   | <b>NORMAL</b> |
| FLUID CONDITION | <b>NORMAL</b> |

Machine Id  
**JOHN DEERE 744P 1DW744PACPLX06325**

Component  
**Rear Differential**

Fluid  
**JOHN DEERE HY-GARD HYDRAULIC/RANSMISSION (--- GAL)**

### RECOMMENDATION

Resample at the next service interval to monitor.

| Test           | UOM | Method      | Limit/Abn | Current            | History1    | History2 |
|----------------|-----|-------------|-----------|--------------------|-------------|----------|
| Sample Number  |     | Client Info |           | <b>JR0197360</b>   | JR0186396   | ---      |
| Sample Date    |     | Client Info |           | <b>15 Jan 2024</b> | 19 Sep 2023 | ---      |
| Machine Age    | hrs | Client Info |           | <b>1103</b>        | 541         | ---      |
| Oil Age        | hrs | Client Info |           | <b>562</b>         | 541         | ---      |
| Filter Age     | hrs | Client Info |           | <b>0</b>           | 0           | ---      |
| Oil Changed    |     | Client Info |           | <b>Not Chngd</b>   | Changed     | ---      |
| Filter Changed |     | Client Info |           | <b>None</b>        | Changed     | ---      |
| Sample Status  |     |             |           | <b>NORMAL</b>      | NORMAL      | ---      |

### WEAR

All component wear rates are normal.

|              |        |             |      |              |      |     |
|--------------|--------|-------------|------|--------------|------|-----|
| PQ           |        | ASTM D8184  |      | <b>30</b>    | 14   | --- |
| Iron         | ppm    | ASTM D5185m | >500 | <b>58</b>    | 44   | --- |
| Chromium     | ppm    | ASTM D5185m | >10  | <b>&lt;1</b> | 0    | --- |
| Nickel       | ppm    | ASTM D5185m | >10  | <b>0</b>     | 0    | --- |
| Titanium     | ppm    | ASTM D5185m |      | <b>0</b>     | <1   | --- |
| Silver       | ppm    | ASTM D5185m |      | <b>0</b>     | 0    | --- |
| Aluminum     | ppm    | ASTM D5185m | >25  | <b>&lt;1</b> | <1   | --- |
| Lead         | ppm    | ASTM D5185m | >25  | <b>2</b>     | <1   | --- |
| Copper       | ppm    | ASTM D5185m | >100 | <b>72</b>    | 40   | --- |
| Tin          | ppm    | ASTM D5185m | >10  | <b>&lt;1</b> | <1   | --- |
| Vanadium     | ppm    | ASTM D5185m |      | <b>&lt;1</b> | <1   | --- |
| White Metal  | scalar | *Visual     | NONE | <b>NONE</b>  | NONE | --- |
| Yellow Metal | scalar | *Visual     | NONE | <b>NONE</b>  | NONE | --- |

### CONTAMINATION







There is no indication of any contamination in the oil.

|                  |        |             |       |              |       |     |
|------------------|--------|-------------|-------|--------------|-------|-----|
| Silicon          | ppm    | ASTM D5185m | >75   | <b>6</b>     | 6     | --- |
| Potassium        | ppm    | ASTM D5185m | >20   | <b>0</b>     | 0     | --- |
| Water            |        | WC Method   | >.2   | <b>NEG</b>   | NEG   | --- |
| Silt             | scalar | *Visual     | NONE  | <b>NONE</b>  | LIGHT | --- |
| Debris           | scalar | *Visual     | NONE  | <b>NONE</b>  | NONE  | --- |
| Sand/Dirt        | scalar | *Visual     | NONE  | <b>NONE</b>  | NONE  | --- |
| Appearance       | scalar | *Visual     | NORML | <b>NORML</b> | NORML | --- |
| Odor             | scalar | *Visual     | NORML | <b>NORML</b> | NORML | --- |
| Emulsified Water | scalar | *Visual     | >.2   | <b>NEG</b>   | NEG   | --- |

### FLUID CONDITION

The condition of the oil is acceptable for the time in service.

|             |     |             |    |              |      |     |
|-------------|-----|-------------|----|--------------|------|-----|
| Sodium      | ppm | ASTM D5185m |    | <b>5</b>     | 7    | --- |
| Boron       | ppm | ASTM D5185m |    | <b>1</b>     | 2    | --- |
| Barium      | ppm | ASTM D5185m |    | <b>0</b>     | 0    | --- |
| Molybdenum  | ppm | ASTM D5185m |    | <b>&lt;1</b> | 2    | --- |
| Manganese   | ppm | ASTM D5185m |    | <b>2</b>     | 2    | --- |
| Magnesium   | ppm | ASTM D5185m |    | <b>86</b>    | 108  | --- |
| Calcium     | ppm | ASTM D5185m |    | <b>3463</b>  | 3655 | --- |
| Phosphorus  | ppm | ASTM D5185m |    | <b>940</b>   | 1042 | --- |
| Zinc        | ppm | ASTM D5185m |    | <b>1241</b>  | 1275 | --- |
| Sulfur      | ppm | ASTM D5185m |    | <b>3505</b>  | 4206 | --- |
| Visc @ 40°C | cSt | ASTM D445   | 59 | <b>53.8</b>  | 54.1 | --- |



Certificate L2367

**Laboratory** : WearCheck USA - 501 Madison Ave., Cary, NC 27513  
**Sample No.** : JR0197360 **Received** : 17 Jan 2024  
**Lab Number** : 06063016 **Diagnosed** : 18 Jan 2024  
**Unique Number** : 10834398 **Diagnostician** : Sean Felton  
**Test Package** : CONST ( Additional Tests: PQ )

To discuss this sample report, contact Customer Service at 1-800-237-1369.

\* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

**JRE - GARNER**  
 4161 AUBURN CHURCH RD  
 GARNER, NC  
 US 27529  
 Contact: RENN MASHBURN  
 renn.mashburn@jamesriverequipment.com  
 T:  
 F: (919)779-5432