



WEAR	NORMAL
CONTAMINATION	NORMAL
FLUID CONDITION	NORMAL



Area
[W62994]
 Machine Id
JOHN DEERE 672G 1DW672GXVCE644735
 Component
Rear Differential
 Fluid
JOHN DEERE HY-GARD HYD/TRANS (10 GAL)

RECOMMENDATION

Resample at the next service interval to monitor. (Customer Sample Comment: W62994)

Test	UOM	Method	Limit/Abn	Current	History1	History2
Sample Number		Client Info		JR0198942	JR0161619	JRMC373417
Sample Date		Client Info		11 Jan 2024	16 May 2023	23 Sep 2015
Machine Age	hrs	Client Info		6678	5863	2353
Oil Age	hrs	Client Info		3076	0	0
Filter Age	hrs	Client Info		0	0	0
Oil Changed		Client Info		Changed	Not Changd	Changed
Filter Changed		Client Info		Changed	Not Changd	Changed
Sample Status				NORMAL	NORMAL	NORMAL

WEAR

All component wear rates are normal.

PQ		ASTM D8184		21	17	28.0
Iron	ppm	ASTM D5185m	>1501	48	39	101
Chromium	ppm	ASTM D5185m	>11	0	<1	<1
Nickel	ppm	ASTM D5185m	>10	0	0	<1
Titanium	ppm	ASTM D5185m		0	0	0
Silver	ppm	ASTM D5185m		0	<1	<1
Aluminum	ppm	ASTM D5185m	>21	<1	<1	<1
Lead	ppm	ASTM D5185m	>51	<1	<1	3
Copper	ppm	ASTM D5185m	>101	8	6	17
Tin	ppm	ASTM D5185m	>10	0	<1	<1
Vanadium	ppm	ASTM D5185m		0	0	0
White Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE

CONTAMINATION







There is no indication of any contamination in the oil.

Silicon	ppm	ASTM D5185m	>31	4	4	5
Potassium	ppm	ASTM D5185m	>20	0	<1	<1
Water		WC Method	>0.1	NEG	NEG	NEG
Silt	scalar	*Visual	NONE	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.1	NEG	NEG	NEG

FLUID CONDITION

The condition of the oil is acceptable for the time in service.

Sodium	ppm	ASTM D5185m	>51	3	2	7
Boron	ppm	ASTM D5185m	6	0	<1	0
Barium	ppm	ASTM D5185m	0	<1	0	5
Molybdenum	ppm	ASTM D5185m	0	<1	<1	<1
Manganese	ppm	ASTM D5185m		<1	<1	2
Magnesium	ppm	ASTM D5185m	145	94	95	87
Calcium	ppm	ASTM D5185m	3570	3326	3436	3338
Phosphorus	ppm	ASTM D5185m	1290	1063	1026	999
Zinc	ppm	ASTM D5185m	1640	1217	1265	1152
Sulfur	ppm	ASTM D5185m		3622	4288	5308
Visc @ 40°C	cSt	ASTM D445	57.0	52.4	53.0	50.26



Certificate L2367

Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513
Sample No. : JR0198942 **Received** : 17 Jan 2024
Lab Number : 06063031 **Diagnosed** : 18 Jan 2024
Unique Number : 10834413 **Diagnostician** : Sean Felton
Test Package : CONST (Additional Tests: PQ)

To discuss this sample report, contact Customer Service at 1-800-237-1369.

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

JRE - CHARLOTTE
 9550 STATESVILLE ROAD
 CHARLOTTE, NC
 US 28269
 Contact: CHARLOTTE SHOP
 myoung@jamesriverequipment.com
 T: (704)597-0211
 F: (704)596-6198