



WEAR	NORMAL
CONTAMINATION	NORMAL
FLUID CONDITION	NORMAL



Area
[W48920]
Machine Id
JOHN DEERE 750K 1T0750KXEJF332859
Component
Left Outer Final Drive
Fluid
JOHN DEERE HY-GARD HYD/TRANS (--- GAL)

RECOMMENDATION

Resample at the next service interval to monitor.

Test	UOM	Method	Limit/Abn	Current	History1	History2
Sample Number		Client Info		JR0165979	JR0165879	JR0107369
Sample Date		Client Info		10 Jan 2024	05 May 2023	10 Nov 2021
Machine Age	hrs	Client Info		5025	3992	2998
Oil Age	hrs	Client Info		0	0	1000
Filter Age	hrs	Client Info		0	0	0
Oil Changed		Client Info		Changed	Changed	Changed
Filter Changed		Client Info		N/A	N/A	N/A
Sample Status				NORMAL	SEVERE	NORMAL

WEAR

All component wear rates are normal.

PQ		ASTM D8184	>1250	181	327	60
Iron	ppm	ASTM D5185m	>750	231	364	70
Chromium	ppm	ASTM D5185m	>9	1	2	<1
Nickel	ppm	ASTM D5185m	>10	2	3	<1
Titanium	ppm	ASTM D5185m		<1	4	<1
Silver	ppm	ASTM D5185m		0	0	<1
Aluminum	ppm	ASTM D5185m	>40	5	▲ 35	6
Lead	ppm	ASTM D5185m	>15	0	0	<1
Copper	ppm	ASTM D5185m	>40	<1	<1	<1
Tin	ppm	ASTM D5185m	>10	0	0	<1
Vanadium	ppm	ASTM D5185m		0	<1	<1
White Metal	scalar	*Visual	NONE	NONE	NONE	LIGHT
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE

CONTAMINATION







There is no indication of any contamination in the oil.

Silicon	ppm	ASTM D5185m	>75	54	● 215	17
Potassium	ppm	ASTM D5185m	>20	1	6	1
Water		WC Method	>0.075	NEG	NEG	NEG
Silt	scalar	*Visual	NONE	NONE	MODER	NONE
Debris	scalar	*Visual	NONE	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.075	NEG	NEG	NEG

FLUID CONDITION

The condition of the oil is acceptable for the time in service.

Sodium	ppm	ASTM D5185m	>51	1	1	2
Boron	ppm	ASTM D5185m	6	4	0	5
Barium	ppm	ASTM D5185m	0	0	0	0
Molybdenum	ppm	ASTM D5185m	0	4	<1	<1
Manganese	ppm	ASTM D5185m		2	3	<1
Magnesium	ppm	ASTM D5185m	145	121	100	102
Calcium	ppm	ASTM D5185m	3570	3236	3472	3464
Phosphorus	ppm	ASTM D5185m	1290	1050	1008	991
Zinc	ppm	ASTM D5185m	1640	1215	1242	1183
Sulfur	ppm	ASTM D5185m		3631	4229	3106
Visc @ 40°C	cSt	ASTM D445	57.0	55.0	52.3	52.3



Certificate L2367

Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513
Sample No. : JR0165979 **Received** : 17 Jan 2024
Lab Number : 06063069 **Diagnosed** : 18 Jan 2024
Unique Number : 10834451 **Diagnostician** : Wes Davis
Test Package : CONST (Additional Tests: PQ)

To discuss this sample report, contact Customer Service at 1-800-237-1369.

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

JRE - ASHLAND
 11047 LEADBETTER RD
 ASHLAND, VA
 US 23005

Contact: DAVID ZIEG
 dzieg@jamesriverequipment.com

T: (804)798-6001
 F: (804)798-0292