WEAR CONTAMINATION FLUID CONDITION


NORMAL NORMAL NORMAL

[W49098]

JOHN DEERE 750L 1T0750LXENF429886

Component Left Outer Final Drive

JOHN DEERE HY-GARD HYD/TRANS (GAL)							
RECOMMENDATION	Test	UOM	Method	Limit/Abn	Current	History1	History2
Resample at the next service interval to monitor.	Sample Number		Client Info		JR0200170	JR0165052	
	Sample Date		Client Info		11 Jan 2024	09 May 2023	
	Machine Age	hrs	Client Info		1939	969	
	Oil Age	hrs	Client Info		0	0	
	Filter Age	hrs	Client Info		0	0	
	Oil Changed		Client Info		Changed	Changed	
	Filter Changed		Client Info		N/A	N/A	
	Sample Status				NORMAL	NORMAL	
WEAR	PQ		ASTM D8184	>1250	91	89	
All component wear rates are normal.	Iron	ppm	ASTM D5185m	>750	130	98	
, in component near race are normal.	Chromium	ppm	ASTM D5185m	>9	<1	1	
	Nickel	ppm	ASTM D5185m	>10	<1	1	
	Titanium	ppm	ASTM D5185m		<1	<1	
	Silver	ppm	ASTM D5185m		0	0	
	Aluminum	ppm	ASTM D5185m	>40	5	7	
	Lead	ppm	ASTM D5185m		0	1	
	Copper	ppm	ASTM D5185m		<1	<1	
	Tin	ppm	ASTM D5185m	>10	0	<1	
	Vanadium	ppm	ASTM D5185m		0	<1	
	White Metal	scalar	*Visual	NONE	NONE	MODER	
	Yellow Metal	scalar	*Visual	NONE	NONE	NONE	
CONTAMINATION There is no indication of any contamination in the oil.	Silicon	ppm	ASTM D5185m	>75	37	21	
	Potassium	ppm	ASTM D5185m	>20	0	4	
	Water		WC Method	>0.075	NEG	NEG	
	Silt	scalar	*Visual	NONE	NONE	NONE	
	Debris	scalar	*Visual	NONE	NONE	NONE	
	Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	
	Appearance	scalar	*Visual	NORML	NORML	NORML	
	Odor	scalar	*Visual	NORML	NORML	NORML	
	Emulsified Water	scalar	*Visual	>0.075	NEG	NEG	
FLUID CONDITION	Sodium	ppm	ASTM D5185m	>51	2	2	
The condition of the oil is acceptable for the time in service.	Boron	ppm	ASTM D5185m	6	4	1	
	Barium	ppm	ASTM D5185m		0	0	
	Molybdenum	ppm	ASTM D5185m	0	4	<1	
	Manganese	ppm	ASTM D5185m		1	2	
	Magnesium	ppm	ASTM D5185m		122	113	
	Calcium	ppm	ASTM D5185m		3328	3600	
	Phosphorus	ppm	ASTM D5185m		1068	1046	
	Zinc	ppm	ASTM D5185m	1640	1242	1319	
	Sulfur	ppm	ASTM D5185m	F7.0	4114	4223	
	Visc @ 40°C	cSt	ASTM D445	57.0	53.4	51.3	





Laboratory Sample No. Lab Number **Unique Number**

: JR0200170 : 06063093 : 10834475 Test Package : CONST (Additional Tests: PQ)

To discuss this sample report, contact Customer Service at 1-800-237-1369.

: WearCheck USA - 501 Madison Ave., Cary, NC 27513 Recieved : 17 Jan 2024 Diagnosed : 18 Jan 2024

Diagnostician : Wes Davis

US 23005 Contact: DAVID ZIEG dzieg@jamesriverequipment.com T: (804)798-6001

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation. Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

Contact/Location: DAVID ZIEG - JAMASH

JRE - ASHLAND

F: (804)798-0292

ASHLAND, VA

11047 LEADBETTER RD