WEAR CONTAMINATION FLUID CONDITION


NORMAL NORMAL NORMAL

[W49098]

JOHN DEERE 750L 1T0750LXENF429886

Component Left Inner Final Drive

JOHN DEERE HY-GARD HYD/TRANS (GAL)							
RECOMMENDATION	Test	UOM	Method	Limit/Abn	Current	History1	History2
Resample at the next service interval to monitor.	Sample Number		Client Info		JR0200169	JR0165051	
	Sample Date		Client Info		11 Jan 2024	09 May 2023	
	Machine Age	hrs	Client Info		1939	969	
	Oil Age	hrs	Client Info		0	0	
	Filter Age	hrs	Client Info		0	0	
	Oil Changed		Client Info		Changed	Changed	
	Filter Changed		Client Info		N/A	N/A	
	Sample Status				NORMAL	NORMAL	
WEAR	PQ		ASTM D8184	>1250	107	68	
All component wear rates are normal.	Iron	ppm	ASTM D5185m	>750	152	100	
The compensation rates are normal	Chromium	ppm	ASTM D5185m	>9	1	1	
	Nickel	ppm	ASTM D5185m	>10	<1	<1	
	Titanium	ppm	ASTM D5185m		0	<1	
	Silver	ppm	ASTM D5185m		0	0	
	Aluminum	ppm	ASTM D5185m	>40	<1	1	
	Lead	ppm	ASTM D5185m	>15	0	5	
	Copper	ppm	ASTM D5185m	>40	<1	<1	
	Tin	ppm	ASTM D5185m	>10	0	<1	
	Vanadium	ppm	ASTM D5185m		0	<1	
	White Metal	scalar	*Visual	NONE	NONE	LIGHT	
	Yellow Metal	scalar	*Visual	NONE	NONE	NONE	
CONTAMINATION There is no indication of any contamination in the oil.	Silicon	ppm	ASTM D5185m	>75	6	5	
	Potassium	ppm	ASTM D5185m	>20	0	3	
	Water		WC Method	>0.075	NEG	NEG	
	Silt	scalar	*Visual	NONE	NONE	NONE	
	Debris	scalar	*Visual	NONE	NONE	LIGHT	
	Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	
	Appearance	scalar	*Visual	NORML	NORML	NORML	
	Odor	scalar	*Visual	NORML	NORML	NORML	
	Emulsified Water	scalar	*Visual	>0.075	NEG	NEG	
FLUID CONDITION	Sodium	ppm	ASTM D5185m	>51	2	2	
The condition of the oil is acceptable for the time in service.	Boron	ppm	ASTM D5185m	6	4	<1	
	Barium	ppm	ASTM D5185m	0	0	0	
	Molybdenum	ppm	ASTM D5185m	0	4	<1	
	Manganese	ppm	ASTM D5185m		1	2	
	Magnesium	ppm	ASTM D5185m	145	114	109	
	Calcium	ppm		3570	3134	3560	
	Phosphorus	ppm	ASTM D5185m	1290	1027	1050	
	Zinc	ppm	ASTM D5185m	1640	1160	1299	
	Sulfur	ppm	ASTM D5185m		3476	4139	
	Visc @ 40°C	cSt	ASTM D445	57.0	51.6	50.4	





Laboratory Sample No. Lab Number **Unique Number**

: JR0200169 : 06063094 : 10834476

: WearCheck USA - 501 Madison Ave., Cary, NC 27513 Recieved : 17 Jan 2024 Diagnosed : 18 Jan 2024

Diagnostician : Sean Felton

Test Package : CONST (Additional Tests: PQ)

Contact: DAVID ZIEG dzieg@jamesriverequipment.com T: (804)798-6001 F: (804)798-0292

To discuss this sample report, contact Customer Service at 1-800-237-1369. * - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

JRE - ASHLAND

ASHLAND, VA

US 23005

11047 LEADBETTER RD