



OIL ANALYSIS REPORT

WEAR	NORMAL
CONTAMINATION	NORMAL
FLUID CONDITION	NORMAL



Area
Store 9 - Marietta
 Machine Id
JOHN DEERE 210G LC EX51 (S/N 1FF210GXKLF528838)
 Component
Hydraulic System
 Fluid
HITACHI HYDRAULIC SUPER EX 46HN (63 GAL)

RECOMMENDATION

Resample at the next service interval to monitor.

Test	UOM	Method	Limit/Abn	Current	History1	History2
Sample Number		Client Info		LEC0047658	LEC0040119	LEC0032017
Sample Date		Client Info		16 Dec 2023	13 Apr 2023	25 Jul 2022
Machine Age	hrs	Client Info		3933	3015	500
Oil Age	hrs	Client Info		3933	3015	0
Filter Age	hrs	Client Info		1000	500	0
Oil Changed		Client Info		Not Changed	Not Changed	Not Changed
Filter Changed		Client Info		Changed	Changed	N/A
Sample Status				NORMAL	NORMAL	NORMAL

WEAR

All component wear rates are normal.

PQ		ASTM D8184	>50	12	11	16
Iron	ppm	ASTM D5185m	>32	<1	3	4
Chromium	ppm	ASTM D5185m	>9	<1	<1	0
Nickel	ppm	ASTM D5185m	>5	0	<1	0
Titanium	ppm	ASTM D5185m		0	0	0
Silver	ppm	ASTM D5185m		0	0	0
Aluminum	ppm	ASTM D5185m	>9	2	0	0
Lead	ppm	ASTM D5185m	>28	0	<1	0
Copper	ppm	ASTM D5185m	>50	<1	1	2
Tin	ppm	ASTM D5185m	>5	0	<1	<1
Vanadium	ppm	ASTM D5185m		0	0	0
White Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE

CONTAMINATION











The system cleanliness is acceptable for your target ISO 4406 cleanliness code. The system and fluid cleanliness is acceptable.

Silicon	ppm	ASTM D5185m	>11	0	<1	<1
Potassium	ppm	ASTM D5185m	>20	<1	2	0
Water		WC Method	>0.075	NEG	NEG	NEG
Particles >4µm		ASTM D7647	>80000	7451	3531	14347
Particles >6µm		ASTM D7647	>20000	465	284	1659
Particles >14µm		ASTM D7647	>640	15	21	111
Particles >21µm		ASTM D7647	>160	4	6	31
Particles >38µm		ASTM D7647	>40	0	1	2
Particles >71µm		ASTM D7647	>10	0	0	0
Oil Cleanliness		ISO 4406 (c)	>23/21/16	20/16/11	19/15/12	21/18/14
Silt	scalar	*Visual	NONE	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.075	NEG	NEG	NEG

FLUID CONDITION

The AN level is acceptable for this fluid. The condition of the oil is suitable for further service.

Sodium	ppm	ASTM D5185m	>21	0	5	0
Boron	ppm	ASTM D5185m		0	0	0
Barium	ppm	ASTM D5185m		3	0	0
Molybdenum	ppm	ASTM D5185m		0	<1	0
Manganese	ppm	ASTM D5185m		0	<1	0
Magnesium	ppm	ASTM D5185m		0	3	0
Calcium	ppm	ASTM D5185m		<1	1	<1
Phosphorus	ppm	ASTM D5185m	827	167	485	462
Zinc	ppm	ASTM D5185m	0	0	4	23
Sulfur	ppm	ASTM D5185m	13	0	117	138
Acid Number (AN)	mg KOH/g	ASTM D8045	0.06	0.24	0.20	0.20
Visc @ 40°C	cSt	ASTM D445	47	46.97	46.8	47.0



Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513
Sample No. : LEC0047658 **Received** : 17 Jan 2024
Lab Number : 06063514 **Diagnosed** : 24 Jan 2024
Unique Number : 10834896 **Diagnostician** : Doug Bogart
Test Package : CONST (Additional Tests: PQ)

LANE PIPELINE
 2946 E MAIN ST
 BRIDGEPORT, WV
 US 26330
 Contact: JESSE WILBURN
 jesseowilburn@gmail.com
 T: (740)440-0927
 F:

To discuss this sample report, contact Customer Service at 1-800-237-1369.

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)