



WEAR	NORMAL
CONTAMINATION	NORMAL
FLUID CONDITION	NORMAL

Area
CPT OA FRANKS
Machine Id
[CPT OA FRANKS] 004 586734-4
Component
Port Reduction Gear
Fluid
CHEVRON URSA SUPER PLUS 40 (17 GAL)

RECOMMENDATION

Resample at the next service interval to monitor.

Test	UOM	Method	Limit/Abn	Current	History1	History2
Sample Number		Client Info		MW06063751	MW06032823	MW05898183
Sample Date		Client Info		01 Dec 2023	30 Oct 2023	30 Jun 2023
Machine Age	hrs	Client Info		37663	36825	34043
Oil Age	hrs	Client Info		0	424	1598
Filter Age	hrs	Client Info		0	0	0
Oil Changed		Client Info		N/A	N/A	N/A
Filter Changed		Client Info		N/A	N/A	N/A
Sample Status				NORMAL	NORMAL	NORMAL

WEAR

All component wear rates are normal.

Iron	ppm	ASTM D5185m	>150	2	2	5
Chromium	ppm	ASTM D5185m	>10	0	0	<1
Nickel	ppm	ASTM D5185m	>10	0	0	0
Titanium	ppm	ASTM D5185m		0	0	0
Silver	ppm	ASTM D5185m		0	<1	<1
Aluminum	ppm	ASTM D5185m	>25	4	3	1
Lead	ppm	ASTM D5185m	>100	0	0	<1
Copper	ppm	ASTM D5185m	>50	<1	1	1
Tin	ppm	ASTM D5185m	>10	0	0	<1
Vanadium	ppm	ASTM D5185m		0	0	0
White Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE

CONTAMINATION







There is no indication of any contamination in the oil.

Silicon	ppm	ASTM D5185m	>50	3	4	4
Potassium	ppm	ASTM D5185m	>20	<1	0	3
Water		WC Method	>0.1	NEG	NEG	NEG
Silt	scalar	*Visual	NONE	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE	LIGHT
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.1	NEG	NEG	NEG

FLUID CONDITION

The AN level is acceptable for this fluid. The condition of the oil is suitable for further service.

Sodium	ppm	ASTM D5185m		2	4	1
Boron	ppm	ASTM D5185m		279	336	282
Barium	ppm	ASTM D5185m		0	0	0
Molybdenum	ppm	ASTM D5185m		30	31	30
Manganese	ppm	ASTM D5185m		0	<1	<1
Magnesium	ppm	ASTM D5185m		14	13	12
Calcium	ppm	ASTM D5185m		2316	2328	2448
Phosphorus	ppm	ASTM D5185m	1000	690	679	704
Zinc	ppm	ASTM D5185m	1090	752	751	810
Sulfur	ppm	ASTM D5185m		3073	2920	3607
Acid Number (AN)	mg KOH/g	ASTM D8045		1.06	0.99	1.10
Visc @ 40°C	cSt	ASTM D445	143	131	133	131



Certificate L2367

Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513
Sample No. : MW06063751 **Recieved** : 17 Jan 2024
Lab Number : 06063751 **Diagnosed** : 19 Jan 2024
Unique Number : 10835133 **Diagnostician** : Wes Davis
Test Package : MAR 2

To discuss this sample report, contact Customer Service at 1-800-237-1369.

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

INGRAM BARGE
 900 S 3RD ST
 PADUCAH, KY
 US 42003

Contact: ANTHONY VAN CURA
 anthony.vancura@ingrambarga.com
 T: (270)415-4467
 F: (615)695-3697