



WEAR	NORMAL
CONTAMINATION	NORMAL
FLUID CONDITION	NORMAL



Machine Id
JOHN DEERE 750K 1T0750KXHKF363027

Component
Diesel Engine

Fluid
JOHN DEERE ENGINE OIL PLUS 50 II 15W40 (--- GAL)

RECOMMENDATION

Resample at the next service interval to monitor.

Test	UOM	Method	Limit/Abn	Current	History1	History2
Sample Number		Client Info		JR0198706	JR0188670	JR0171199
Sample Date		Client Info		15 Jan 2024	29 Sep 2023	19 Jun 2023
Machine Age	hrs	Client Info		6578	6002	5489
Oil Age	hrs	Client Info		576	513	4544
Filter Age	hrs	Client Info		0	0	0
Oil Changed		Client Info		Changed	Changed	Changed
Filter Changed		Client Info		Changed	Changed	Changed
Sample Status				NORMAL	ATTENTION	SEVERE

WEAR

All component wear rates are normal.

Iron	ppm	ASTM D5185m	>51	18	15	39
Chromium	ppm	ASTM D5185m	>11	<1	<1	2
Nickel	ppm	ASTM D5185m	>5	8	3	6
Titanium	ppm	ASTM D5185m		0	0	<1
Silver	ppm	ASTM D5185m	>3	0	0	0
Aluminum	ppm	ASTM D5185m	>31	3	1	▲ 6
Lead	ppm	ASTM D5185m	>26	0	<1	2
Copper	ppm	ASTM D5185m	>26	1	3	18
Tin	ppm	ASTM D5185m	>4	0	<1	2
Vanadium	ppm	ASTM D5185m		0	<1	<1
White Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE

CONTAMINATION







There is no indication of any contamination in the oil.

Silicon	ppm	ASTM D5185m	>22	10	10	● 66
Potassium	ppm	ASTM D5185m	>20	4	10	▲ 165
Fuel		WC Method	>2.1	<1.0	<1.0	<1.0
Water		WC Method	>0.21	NEG	NEG	NEG
Glycol		WC Method		NEG	NEG	● 0.12
Soot %	%	*ASTM D7844	>3	0.3	0.2	0.3
Nitration	Abs/cm	*ASTM D7624	>20	8.6	8.6	13.6
Sulfation	Abs/.1mm	*ASTM D7415	>30	22.7	21.8	26.3
Silt	scalar	*Visual	NONE	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.21	NEG	NEG	NEG

FLUID CONDITION

The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

Sodium	ppm	ASTM D5185m	>31	21	▲ 125	▲ 1778
Boron	ppm	ASTM D5185m		230	207	107
Barium	ppm	ASTM D5185m		4	0	0
Molybdenum	ppm	ASTM D5185m		261	256	397
Manganese	ppm	ASTM D5185m		<1	<1	2
Magnesium	ppm	ASTM D5185m		862	847	824
Calcium	ppm	ASTM D5185m		1346	1472	1516
Phosphorus	ppm	ASTM D5185m		879	865	847
Zinc	ppm	ASTM D5185m		1123	1101	1114
Sulfur	ppm	ASTM D5185m		3188	2974	3670
Oxidation	Abs/.1mm	*ASTM D7414	>25	17.2	16.3	18.0
Base Number (BN)	mg KOH/g	ASTM D2896	13.6	8.2	8.8	11.3
Visc @ 100°C	cSt	ASTM D445	15.4	13.5	13.4	14.1



Certificate L2367

Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513
Sample No. : JR0198706 **Received** : 18 Jan 2024
Lab Number : 06064033 **Diagnosed** : 20 Jan 2024
Unique Number : 10835415 **Diagnostician** : Don Baldrige
Test Package : CONST (Additional Tests: TBN)

JRE - CHARLOTTE
 9550 STATESVILLE ROAD
 CHARLOTTE, NC
 US 28269
 Contact: CHARLOTTE SHOP
 myoung@jamesriverequipment.com
 T: (704)597-0211
 F: (704)596-6198

To discuss this sample report, contact Customer Service at 1-800-237-1369.
 * - Denotes test methods that are outside of the ISO 17025 scope of accreditation.
 Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)