



WEAR	NORMAL
CONTAMINATION	NORMAL
FLUID CONDITION	NORMAL

Machine Id
10524

Component
Diesel Engine

Fluid
PETRO CANADA DURON SHP 15W40 (13 GAL)

RECOMMENDATION

Resample at the next service interval to monitor.

Test	UOM	Method	Limit/Abn	Current	History1	History2
Sample Number		Client Info		GFL0107240	GFL0101260	GFL0086081
Sample Date		Client Info		12 Jan 2024	05 Dec 2023	27 Jun 2023
Machine Age	hrs	Client Info		439	180	17226
Oil Age	hrs	Client Info		259	214	34
Filter Age	hrs	Client Info		259	214	34
Oil Changed		Client Info		Not Changd	Changed	Changed
Filter Changed		Client Info		Not Changd	Changed	Changed
Sample Status				NORMAL	NORMAL	NORMAL

WEAR

Metal levels are typical for a new component breaking in.

Iron	ppm	ASTM D5185m	>110	19	7	11
Chromium	ppm	ASTM D5185m	>4	<1	<1	<1
Nickel	ppm	ASTM D5185m	>2	0	0	<1
Titanium	ppm	ASTM D5185m		0	0	<1
Silver	ppm	ASTM D5185m	>2	0	0	0
Aluminum	ppm	ASTM D5185m	>25	4	2	5
Lead	ppm	ASTM D5185m	>45	0	0	<1
Copper	ppm	ASTM D5185m	>85	<1	0	<1
Tin	ppm	ASTM D5185m	>4	0	0	<1
Vanadium	ppm	ASTM D5185m		0	0	0
White Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE

CONTAMINATION







There is no indication of any contamination in the oil.

Silicon	ppm	ASTM D5185m	>30	4	3	5
Potassium	ppm	ASTM D5185m	>20	6	2	2
Fuel		WC Method	>5	<1.0	<1.0	<1.0
Water		WC Method	>0.2	NEG	NEG	NEG
Glycol		WC Method		NEG	NEG	NEG
Soot %	%	*ASTM D7844	>3	0.5	0.1	0.4
Nitration	Abs/cm	*ASTM D7624	>20	6.7	4.5	5.8
Sulfation	Abs/.1mm	*ASTM D7415	>30	17.4	16.5	17.3
Silt	scalar	*Visual	NONE	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.2	NEG	NEG	NEG

FLUID CONDITION

The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

Sodium	ppm	ASTM D5185m		1	2	2
Boron	ppm	ASTM D5185m	0	3	7	27
Barium	ppm	ASTM D5185m	0	3	2	0
Molybdenum	ppm	ASTM D5185m	60	61	63	59
Manganese	ppm	ASTM D5185m	0	0	0	<1
Magnesium	ppm	ASTM D5185m	1010	897	888	802
Calcium	ppm	ASTM D5185m	1070	983	1097	1074
Phosphorus	ppm	ASTM D5185m	1150	892	952	947
Zinc	ppm	ASTM D5185m	1270	1182	1193	1158
Sulfur	ppm	ASTM D5185m	2060	2908	3499	3575
Oxidation	Abs/.1mm	*ASTM D7414	>25	12.4	11.6	11.9
Base Number (BN)	mg KOH/g	ASTM D2896	9.8	7.7	8.4	8.4
Visc @ 100°C	cSt	ASTM D445	15.4	13.0	13.4	12.7



Certificate L2367

Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513
Sample No. : GFL0107240 **Received** : 18 Jan 2024
Lab Number : 06064077 **Diagnosed** : 19 Jan 2024
Unique Number : 10835459 **Diagnostician** : Wes Davis
Test Package : FLEET

GFL Environmental - 010 - Stockbridge
 1280 Rum Creek Parkway
 Stockbridge, GA
 US 30281
 Contact: TECHNICIAN ACCOUNT
 wcgfldemo@gmail.com

To discuss this sample report, contact Customer Service at 1-800-237-1369.

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

T:
F: