



OIL ANALYSIS REPORT

WEAR	NORMAL
CONTAMINATION	NORMAL
FLUID CONDITION	NORMAL

Machine Id
1724
Component
Diesel Engine
Fluid
DIESEL ENGINE OIL SAE 15W40 (--- GAL)

RECOMMENDATION

Resample at the next service interval to monitor. Please specify the component make and model with your next sample. Please specify the brand, type, and viscosity of the oil on your next sample.

Test	UOM	Method	Limit/Abn	Current	History1	History2
Sample Number		Client Info		WC0810309	WC0860427	WC0844951
Sample Date		Client Info		05 Jan 2024	23 Oct 2023	18 Aug 2023
Machine Age	mls	Client Info		192780	187287	181843
Oil Age	mls	Client Info		0	6000	0
Filter Age	mls	Client Info		0	6000	0
Oil Changed		Client Info		N/A	Changed	Changed
Filter Changed		Client Info		N/A	Changed	Changed
Sample Status				NORMAL	NORMAL	NORMAL

WEAR

All component wear rates are normal.

Iron	ppm	ASTM D5185m	>100	6	4	4
Chromium	ppm	ASTM D5185m	>20	<1	0	<1
Nickel	ppm	ASTM D5185m	>4	0	0	0
Titanium	ppm	ASTM D5185m		0	<1	<1
Silver	ppm	ASTM D5185m	>3	0	0	0
Aluminum	ppm	ASTM D5185m	>20	2	4	6
Lead	ppm	ASTM D5185m	>40	0	<1	0
Copper	ppm	ASTM D5185m	>330	18	4	<1
Tin	ppm	ASTM D5185m	>15	<1	0	<1
Vanadium	ppm	ASTM D5185m		0	0	0
White Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE

CONTAMINATION







There is no indication of any contamination in the oil.

Silicon	ppm	ASTM D5185m	>25	8	9	8
Potassium	ppm	ASTM D5185m	>20	2	1	0
Fuel		WC Method	>5	<1.0	<1.0	<1.0
Water		WC Method	>0.2	NEG	NEG	NEG
Glycol		WC Method		NEG	NEG	NEG
Soot %	%	*ASTM D7844	>3	0.3	0.3	0.3
Nitration	Abs/cm	*ASTM D7624	>20	8.9	8.4	8.9
Sulfation	Abs/.1mm	*ASTM D7415	>30	21.3	20.3	19.7
Silt	scalar	*Visual	NONE	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.2	NEG	NEG	NEG

FLUID CONDITION

The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

Sodium	ppm	ASTM D5185m	>158	2	4	5
Boron	ppm	ASTM D5185m	250	110	146	29
Barium	ppm	ASTM D5185m	10	3	0	0
Molybdenum	ppm	ASTM D5185m	100	82	71	77
Manganese	ppm	ASTM D5185m		0	0	<1
Magnesium	ppm	ASTM D5185m	450	232	256	277
Calcium	ppm	ASTM D5185m	3000	1680	1463	2135
Phosphorus	ppm	ASTM D5185m	1150	884	837	1124
Zinc	ppm	ASTM D5185m	1350	1159	1166	1386
Sulfur	ppm	ASTM D5185m	4250	3419	2830	4450
Oxidation	Abs/.1mm	*ASTM D7414	>25	18.4	16.9	16.0
Base Number (BN)	mg KOH/g	ASTM D2896	8.5	5.4	5.8	7.4
Visc @ 100°C	cSt	ASTM D445	14.4	13.3	13.8	14.1



Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513
Sample No. : WC0810309 **Received** : 18 Jan 2024
Lab Number : 06064112 **Diagnosed** : 19 Jan 2024
Unique Number : 10835494 **Diagnostician** : Wes Davis
Test Package : FLEET

TOWN OF CHAPEL HILL
 6900 MILLHOUSE RD
 CHAPEL HILL, NC
 US 27516
 Contact: Lisa DePasqua
 ldepasqua@townofchapelhill.org
 T: (919)696-4941
 F:

Certificate L2367
 To discuss this sample report, contact Customer Service at 1-800-237-1369.
 * - Denotes test methods that are outside of the ISO 17025 scope of accreditation.
 Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)