



WEAR	NORMAL
CONTAMINATION	NORMAL
FLUID CONDITION	NORMAL

Area
(P633829)

Machine Id
3760C

Component
Natural Gas Engine

Fluid
PETRO CANADA DURON GEO LD 15W40 (40 QTS)

RECOMMENDATION

Resample at the next service interval to monitor.

Test	UOM	Method	Limit/Abn	Current	History1	History2
Sample Number		Client Info		GFL0101774	GFL0090069	GFL0090103
Sample Date		Client Info		12 Jan 2024	02 Nov 2023	18 Oct 2023
Machine Age	hrs	Client Info		15433	14985	14812
Oil Age	hrs	Client Info		600	600	132
Filter Age	hrs	Client Info		600	600	132
Oil Changed		Client Info		Changed	Changed	Not Changd
Filter Changed		Client Info		Changed	Changed	Not Changd
Sample Status				NORMAL	NORMAL	NORMAL

WEAR

All component wear rates are normal.

Iron	ppm	ASTM D5185m	>50	10	15	3
Chromium	ppm	ASTM D5185m	>4	1	1	<1
Nickel	ppm	ASTM D5185m	>2	<1	0	0
Titanium	ppm	ASTM D5185m		0	<1	<1
Silver	ppm	ASTM D5185m	>3	0	0	0
Aluminum	ppm	ASTM D5185m	>9	2	2	<1
Lead	ppm	ASTM D5185m	>30	<1	0	0
Copper	ppm	ASTM D5185m	>35	0	<1	<1
Tin	ppm	ASTM D5185m	>4	<1	0	0
Vanadium	ppm	ASTM D5185m		0	<1	<1
White Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE

CONTAMINATION







There is no indication of any contamination in the oil.

Silicon	ppm	ASTM D5185m	>+100	5	8	11
Potassium	ppm	ASTM D5185m	>20	2	11	0
Water		WC Method	>0.1	NEG	NEG	NEG
Soot %	%	*ASTM D7844		0	0	0
Nitration	Abs/cm	*ASTM D7624	>20	9.5	8.7	6.2
Sulfation	Abs/.1mm	*ASTM D7415	>30	18.9	19.9	18.7
Silt	scalar	*Visual	NONE	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	LIGHT	LIGHT
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.1	NEG	NEG	NEG

FLUID CONDITION

The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

Sodium	ppm	ASTM D5185m		4	6	5
Boron	ppm	ASTM D5185m	50	22	22	47
Barium	ppm	ASTM D5185m	5	0	0	0
Molybdenum	ppm	ASTM D5185m	50	48	48	46
Manganese	ppm	ASTM D5185m	0	<1	<1	<1
Magnesium	ppm	ASTM D5185m	560	560	534	507
Calcium	ppm	ASTM D5185m	1510	1481	1482	1440
Phosphorus	ppm	ASTM D5185m	780	783	718	661
Zinc	ppm	ASTM D5185m	870	936	881	843
Sulfur	ppm	ASTM D5185m	2040	2415	2200	2246
Oxidation	Abs/.1mm	*ASTM D7414	>25	16.2	16.9	15.6
Base Number (BN)	mg KOH/g	ASTM D2896	10.2	6.2	7.5	9.0
Visc @ 100°C	cSt	ASTM D445	15.1	14.0	14.9	14.3



Certificate L2367

Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513
Sample No. : GFL0101774 **Received** : 18 Jan 2024
Lab Number : 06064158 **Diagnosed** : 19 Jan 2024
Unique Number : 10835540 **Diagnostician** : Wes Davis
Test Package : FLEET

GFL Environmental - 030 - Conway Myrtle Beach
 3010 HWY 378
 Conway, SC
 US 29527
 Contact: ARCILIO RUEZ
 aruiz@gflenv.com

To discuss this sample report, contact Customer Service at 1-800-237-1369.
 * - Denotes test methods that are outside of the ISO 17025 scope of accreditation.
 Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)