



OIL ANALYSIS REPORT

WEAR	NORMAL
CONTAMINATION	ABNORMAL
FLUID CONDITION	NORMAL

Area
Mobile Fleet
 Machine Id
6418 6418
 Component
Transmission (Auto)
 Fluid
MOBIL DELVAC SYNTHETIC ATF (8 GAL)

RECOMMENDATION

No corrective action is recommended at this time. Resample at the next service interval to monitor.

Test	UOM	Method	Limit/Abn	Current	History1	History2
Sample Number		Client Info		WC0885953	WC0808831	WC0808912
Sample Date		Client Info		12 Jan 2024	10 Jul 2023	27 Apr 2023
Machine Age	hrs	Client Info		13688	12743	12321
Oil Age	hrs	Client Info		973	4266	3844
Filter Age	hrs	Client Info		973	1882	1460
Oil Changed		Client Info		Not Changd	Changed	Not Changd
Filter Changed		Client Info		Not Changd	Changed	Not Changd
Sample Status				ABNORMAL	NORMAL	ATTENTION

WEAR

All component wear rates are normal.

Iron	ppm	ASTM D5185m	>300	25	99	77
Chromium	ppm	ASTM D5185m	>2	0	<1	0
Nickel	ppm	ASTM D5185m	>4	0	0	0
Titanium	ppm	ASTM D5185m	>3	0	0	0
Silver	ppm	ASTM D5185m	>5	0	0	0
Aluminum	ppm	ASTM D5185m	>70	6	23	21
Lead	ppm	ASTM D5185m	>85	1	7	3
Copper	ppm	ASTM D5185m	>90	8	19	16
Tin	ppm	ASTM D5185m	>10	1	3	2
Vanadium	ppm	ASTM D5185m		0	<1	0
White Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE

CONTAMINATION










There is a high amount of silt (particulates < 14 microns in size) present in the fluid.

Silicon	ppm	ASTM D5185m	>20	2	4	2
Potassium	ppm	ASTM D5185m	>20	<1	3	<1
Water		WC Method	>0.1	NEG	NEG	NEG
Particles >4µm		ASTM D7647	>10000	▲ 52286	7546	▲ 15476
Particles >6µm		ASTM D7647	>2500	▲ 3384	1631	▲ 3275
Particles >14µm		ASTM D7647	>320	50	73	133
Particles >21µm		ASTM D7647	>80	8	24	22
Particles >38µm		ASTM D7647	>20	0	1	0
Particles >71µm		ASTM D7647	>4	0	0	0
Oil Cleanliness		ISO 4406 (c)	>20/18/15	▲ 23/19/13	20/18/13	▲ 21/19/14
Silt	scalar	*Visual	NONE	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	LIGHT	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.1	NEG	NEG	NEG

FLUID CONDITION

The condition of the fluid is acceptable for the time in service.

Sodium	ppm	ASTM D5185m		2	4	3
Boron	ppm	ASTM D5185m		113	129	133
Barium	ppm	ASTM D5185m		0	0	0
Molybdenum	ppm	ASTM D5185m		0	<1	0
Manganese	ppm	ASTM D5185m		<1	1	1
Magnesium	ppm	ASTM D5185m		13	2	1
Calcium	ppm	ASTM D5185m		88	38	51
Phosphorus	ppm	ASTM D5185m		295	320	289
Zinc	ppm	ASTM D5185m		27	0	5
Sulfur	ppm	ASTM D5185m		1246	1753	1134
Visc @ 40°C	cSt	ASTM D445	39	35.3	35.9	35.7



Certificate L2367

Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513
Sample No. : WC0885953 **Received** : 18 Jan 2024
Lab Number : 06064175 **Diagnosed** : 20 Jan 2024
Unique Number : 10835557 **Diagnostician** : Don Baldrige
Test Package : CONST (Additional Tests: PrtCount)

To discuss this sample report, contact Customer Service at 1-800-237-1369.

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

CAROLINA SUNROCK
 PO BOX 25
 BUTNER, NC
 US 27509

Contact: Leigh Dennis
 rdennis@thesunrockgroup.com

T: (919)575-4505

F: (919)575-0162