



WEAR CONTAMINATION FLUID CONDITION

NORMAL NORMAL




Store 4 - Fairmont

JOHN DEERE 300GL 1FF300GXHNF732106

Component Hydraulic System

HITACHI HYDRAULIC SUPER EX 46HN (77 GAL)

HITACHI HYDRAULIC SUPER EX 46HN (77 GAL)							
RECOMMENDATION	Test	UOM	Method	Limit/Abn	Current	History1	History2
Resample at the next service interval to monitor.	Sample Number		Client Info		LEC0046604	LEC0042723	
	Sample Date		Client Info		15 Jan 2024	20 Sep 2023	
	Machine Age	hrs	Client Info		471	471	
	Oil Age	hrs	Client Info		610	471	
	Filter Age	hrs	Client Info		610	471	
	Oil Changed		Client Info		Not Changd	Not Changd	
	Filter Changed		Client Info		Not Changd	Not Changd	
	Sample Status				NORMAL	NORMAL	
WEAR All component wear rates are normal.	PQ		ASTM D8184	>50	14	11	
	Iron	ppm	ASTM D5185m	>32	2	2	
	Chromium	ppm	ASTM D5185m	>9	0	0	
	Nickel	ppm	ASTM D5185m	>5	0	0	
	Titanium	ppm	ASTM D5185m		0	0	
	Silver	ppm	ASTM D5185m		0	0	
	Aluminum	ppm	ASTM D5185m	>9	0	1	
	Lead	ppm	ASTM D5185m	>28	0	0	
	Copper	ppm	ASTM D5185m	>50	2	2	
	Tin	ppm	ASTM D5185m	>5	<1	0	
	Vanadium	ppm	ASTM D5185m		0	0	
	White Metal	scalar	*Visual	NONE	NONE	NONE	
	Yellow Metal	scalar	*Visual	NONE	NONE	NONE	
CONTAMINATION There is no indication of any contamination in the oil. The amount and size of particulates present in the system are acceptable.	Silicon	ppm	ASTM D5185m	>11	<1	<1	
	Potassium	ppm	ASTM D5185m	>20	0	4	
	Water		WC Method	>0.075	NEG	NEG	
	Particles >4µm		ASTM D7647	>80000	3853	4938	
	Particles >6µm		ASTM D7647		189	1121	
	Particles >14μm		ASTM D7647		11	65	
	Particles >21μm		ASTM D7647		4	14	
	Particles >38μm		ASTM D7647		2	1	
	Particles >71μm		ASTM D7647		2	0	
	Oil Cleanliness		ISO 4406 (c)		19/15/11	19/17/13	
	Silt	scalar	*Visual	NONE	NONE	NONE	
	Debris Sand/Dirt	scalar	*Visual *Visual	NONE NONE	NONE NONE	NONE NONE	
	Appearance	scalar scalar	*Visual	NORML	NORML	NORML	
	Odor	scalar	*Visual	NORML	NORML	NORML	
	Emulsified Water		*Visual	>0.075	NEG	NEG	
FLUID CONDITION	Sodium	ppm	ASTM D5185m	>21	<1	2	
The AN level is acceptable for this fluid. The condition of the oil is suitable for further service.	Boron	ppm	ASTM D5185m		0	0	
	Barium	ppm	ASTM D5185m		0	0	
	Molybdenum	ppm	ASTM D5185m		0	0	
	Manganese	ppm	ASTM D5185m		<1 .1	0	
	Magnesium Calcium	ppm	ASTM D5185m ASTM D5185m		<1 2	2	
	Phosphorus	ppm	ASTM D5185m	927	2 539	1 543	
	Zinc	ppm	ASTM D5185m		23	27	
	Sulfur	ppm	ASTM D5185m		94	106	
	Acid Number (AN)	mg KOH/g	ASTM D3103111		0.14	0.14	
	Visc @ 40°C	cSt	ASTM D6045		47.2	46.9	
	V130 @ 40 0	COL	AUTIVI D440	77	77.2	40.5	





Certificate L2367

Laboratory

Sample No. Lab Number **Unique Number**

: LEC0046604 : 06064210

: WearCheck USA - 501 Madison Ave., Cary, NC 27513 Recieved Diagnosed : 10835592

: 18 Jan 2024 : 20 Jan 2024 Diagnostician : Don Baldridge

Test Package : CONST (Additional Tests: PQ) To discuss this sample report, contact Customer Service at 1-800-237-1369.

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation. Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

LESLIE EQUIPMENT COMPANY

105 TENNIS CENTER DR. MARIETTA, OH US 45750-9765 Contact: LEANNE KENDALL

KendalLeanne@lec1.com

T:

F: (740)373-5570