



OIL ANALYSIS REPORT

WEAR	NORMAL
CONTAMINATION	NORMAL
FLUID CONDITION	NORMAL

Machine Id
6384
 Component
Diesel Engine
 Fluid
CASTROL VECTON 15W40 CK4 (--- QTS)

RECOMMENDATION

Resample at the next service interval to monitor. Please specify the component make and model with your next sample.

Test	UOM	Method	Limit/Abn	Current	History1	History2
Sample Number		Client Info		WC0813343	WC0813363	WC0813337
Sample Date		Client Info		17 Jan 2024	16 Jan 2024	15 Oct 2023
Machine Age	hrs	Client Info		2020	1364	1748
Oil Age	hrs	Client Info		0	0	0
Filter Age	hrs	Client Info		0	0	0
Oil Changed		Client Info		N/A	N/A	N/A
Filter Changed		Client Info		N/A	N/A	N/A
Sample Status				NORMAL	NORMAL	NORMAL

WEAR

All component wear rates are normal.

Iron	ppm	ASTM D5185m	>100	3	2	5
Chromium	ppm	ASTM D5185m	>20	0	0	<1
Nickel	ppm	ASTM D5185m	>4	0	0	<1
Titanium	ppm	ASTM D5185m		0	0	<1
Silver	ppm	ASTM D5185m	>3	0	0	0
Aluminum	ppm	ASTM D5185m	>20	1	<1	2
Lead	ppm	ASTM D5185m	>40	<1	<1	<1
Copper	ppm	ASTM D5185m	>330	<1	<1	<1
Tin	ppm	ASTM D5185m	>15	<1	<1	<1
Vanadium	ppm	ASTM D5185m		0	0	0
White Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE

CONTAMINATION







There is no indication of any contamination in the oil.

Silicon	ppm	ASTM D5185m	>25	3	3	4
Potassium	ppm	ASTM D5185m	>20	1	<1	<1
Fuel		WC Method	>5	<1.0	<1.0	<1.0
Water		WC Method	>0.2	NEG	NEG	NEG
Glycol		WC Method		NEG	NEG	NEG
Soot %	%	*ASTM D7844	>3	0	0	0
Nitration	Abs/cm	*ASTM D7624	>20	8.7	9.3	9.3
Sulfation	Abs/.1mm	*ASTM D7415	>30	19.0	18.9	18.8
Silt	scalar	*Visual	NONE	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.2	NEG	NEG	NEG

FLUID CONDITION

The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

Sodium	ppm	ASTM D5185m		2	2	3
Boron	ppm	ASTM D5185m		25	21	22
Barium	ppm	ASTM D5185m		0	0	3
Molybdenum	ppm	ASTM D5185m		46	45	46
Manganese	ppm	ASTM D5185m		0	0	<1
Magnesium	ppm	ASTM D5185m		567	540	488
Calcium	ppm	ASTM D5185m		1526	1527	1460
Phosphorus	ppm	ASTM D5185m		766	753	675
Zinc	ppm	ASTM D5185m		932	918	831
Sulfur	ppm	ASTM D5185m		2316	2248	2078
Oxidation	Abs/.1mm	*ASTM D7414	>25	16.3	16.3	16.1
Base Number (BN)	mg KOH/g	ASTM D2896	10	7.4	6.9	6.7
Visc @ 100°C	cSt	ASTM D445	15.5	14.2	14.2	14.4



Certificate L2367

Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513
Sample No. : WC0813343 **Received** : 18 Jan 2024
Lab Number : 06064688 **Diagnosed** : 19 Jan 2024
Unique Number : 10836070 **Diagnostician** : Wes Davis
Test Package : FLEET

To discuss this sample report, contact Customer Service at 1-800-237-1369.

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

CITY OF BERKELEY
 1199 SECOND ST
 BERKELEY, CA
 US 94710

Contact: BAL JOHAL
 bjoahal@ci.berkeley.ca.us
 T: (510)981-6375
 F: (510)558-1330