OIL ANALYSIS REPORT

WEAR	NORMAL
CONTAMINATION	NORMAL
FLUID CONDITION	NORMAL

Machine Id
2109
Component
Diesel Engine
Fluid
DIESEL ENGINE OIL SAE 5W30 (--- QTS)

RECOMMENDATION

Resample at the next service interval to monitor.

WEAR

All component wear rates are normal.

CONTAMINATION

There is no indication of any contamination in the oil.

FLUID CONDITION

The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

Test	UOM	Method	Limit/Abn	Current	History1	History2
Sample Number		Client Info		**WC0876668**	WC0686104	WC0604082
Sample Date		Client Info		**06 Jan 2024**	21 Aug 2022	01 Sep 2021
Machine Age	mls	Client Info		**460216**	324001	342463
Oil Age	mls	Client Info		**50000**	100000	100000
Filter Age	mls	Client Info		**50000**	50000	100000
Oil Changed		Client Info		**Changed**	Not Changd	Changed
Filter Changed		Client Info		**Changed**	Not Changd	Changed
Sample Status				**NORMAL**	NORMAL	ATTENTION
Iron	ppm	ASTM D5185m	>100	**50**	18	48
Chromium	ppm	ASTM D5185m	>20	**<1**	<1	<1
Nickel	ppm	ASTM D5185m	>4	**0**	0	0
Titanium	ppm	ASTM D5185m		**0**	13	1
Silver	ppm	ASTM D5185m	>3	**0**	<1	0
Aluminum	ppm	ASTM D5185m	>20	**4**	2	3
Lead	ppm	ASTM D5185m	>40	**<1**	2	<1
Copper	ppm	ASTM D5185m	>330	**9**	7	6
Tin	ppm	ASTM D5185m	>15	**2**	1	<1
Vanadium	ppm	ASTM D5185m		**0**	0	<1
White Metal	scalar	*Visual	NONE	**NONE**	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	**NONE**	NONE	NONE
Silicon	ppm	ASTM D5185m	>25	**11**	6	6
Potassium	ppm	ASTM D5185m	>20	**5**	0	6
Fuel		WC Method	>5	**<1.0**	<1.0	<1.0
Water		WC Method	>0.2	**NEG**	NEG	NEG
Glycol		WC Method		**NEG**	NEG	NEG
Soot %	%	*ASTM D7844	>3	**0.9**	0.8	0.6
Nitration	Abs/cm	*ASTM D7624	>20	**12.0**	12.3	17.6
Sulfation	Abs/.1mm	*ASTM D7415	>30	**28.9**	26.1	31.7
Silt	scalar	*Visual	NONE	**NONE**	NONE	NONE
Debris	scalar	*Visual	NONE	**NONE**	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	**NONE**	NONE	NONE
Appearance	scalar	*Visual	NORML	**NORML**	NORML	NORML
Odor	scalar	*Visual	NORML	**NORML**	NORML	NORML
Emulsified Water	scalar	*Visual	>0.2	**NEG**	NEG	NEG
Sodium	ppm	ASTM D5185m		**10**	2	6
Boron	ppm	ASTM D5185m	250	**21**	32	15
Barium	ppm	ASTM D5185m	10	**0**	0	0
Molybdenum	ppm	ASTM D5185m	100	**76**	42	65
Manganese	ppm	ASTM D5185m		**1**	<1	<1
Magnesium	ppm	ASTM D5185m	450	**830**	723	1130
Calcium	ppm	ASTM D5185m	3000	**1342**	1426	999
Phosphorus	ppm	ASTM D5185m	1150	**1125**	909	1039
Zinc	ppm	ASTM D5185m	1350	**1381**	1188	1408
Sulfur	ppm	ASTM D5185m	4250	**3066**	2932	2620
Oxidation	Abs/.1mm	*ASTM D7414	>25	**26.3**	24.1	39.1
Base Number (BN)	mg KOH/g	ASTM D2896	8.5	**5.3**	7.6	2.5
Visc @ 100°C	cSt	ASTM D445	10.9	**12.8**	12.0	▲ 13.1

Base Number



Viscosity @ 100°C



Ferrous Alloys



Non-ferrous Metals



Viscosity @ 100°C



Base Number



Certificate L2367

Laboratory	: WearCheck USA - 501 Madison Ave., Cary, NC 27513		
Sample No.	: WC0876668	**Recieved**	: 18 Jan 2024
Lab Number	: 06064704	**Diagnosed**	: 21 Jan 2024
Unique Number	: 10836086	**Diagnostician**	: Don Baldridge
Test Package	: FLEET		

To discuss this sample report, contact Customer Service at 1-800-237-1369.
** - Denotes test methods that are outside of the ISO 17025 scope of accreditation.*
Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

MABE TRUCKING
PO BOX 1081
EDEN, NC
US 27289
Contact: MAINTENANCE
maintenancemanager@mabetrucking.com
T:
F: (336)635-1791