**WEAR** CONTAMINATION **FLUID CONDITION** 

**NORMAL NORMAL NORMAL** 


Machine Id


526090


Component Diesel Engine


PETRO CANADA	<b>DURON SHP</b>	15W40 (	( GAL)


RECOMMENDATION	Test	UOM	Method	Limit/Abn	Current	History1	History2
Resample at the next service interval to monitor.  WEAR	Sample Number		Client Info		GFL0108167	GFL0087704	
	Sample Date		Client Info		11 Jan 2024	04 Sep 2023	
	Machine Age	hrs	Client Info		11302	265422	
	Oil Age	hrs	Client Info		0	0	
	Filter Age	hrs	Client Info		0	0	
	Oil Changed		Client Info		Not Changd	Changed	
	Filter Changed		Client Info		Not Changd	Changed	
	Sample Status				NORMAL	NORMAL	
	Iron	ppm	ASTM D5185m	>80	35	75	
	Chromium	ppm	ASTM D5185m		<1	<1	
All component wear rates are normal.	Nickel	ppm	ASTM D5185m		0	0	
	Titanium	ppm	ASTM D5185m		0	0	
	Silver	ppm	ASTM D5185m	>3	0	0	
	Aluminum	ppm	ASTM D5185m	>30	5	8	
	Lead	ppm	ASTM D5185m	>30	<1	<1	
	Copper	ppm	ASTM D5185m	>150	4	4	
	Tin	ppm	ASTM D5185m	>5	0	0	
	Vanadium	ppm	ASTM D5185m		<1	<1	
	White Metal	scalar	*Visual	NONE	NONE	NONE	
	Yellow Metal	scalar	*Visual	NONE	NONE	NONE	
CONTAMINATION	0:1:		AOTM DE40E		40	40	
CONTAMINATION	Silicon	ppm	ASTM D5185m		10	10	
There is no indication of any contamination in the oil.	Potassium Fuel	ppm	ASTM D5185m		4	7	
			WC Method		<1.0	<1.0	
	Water Glycol		WC Method WC Method	>0.2	NEG NEG	NEG NEG	
	Soot %	%	*ASTM D7844	- 3	0.1	0.1	
	Nitration	Abs/cm	*ASTM D7624	>20	6.4	7.8	
	Sulfation	Abs/.1mm	*ASTM D7024		17.8	17.3	
	Silt	scalar	*Visual	NONE	NONE	NONE	
	Debris	scalar	*Visual	NONE	NONE	NONE	
	Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	
	Appearance	scalar	*Visual	NORML	NORML	NORML	
	Odor	scalar	*Visual	NORML	NORML	NORML	
	<b>Emulsified Water</b>	scalar	*Visual	>0.2	NEG	NEG	
THE CONDITION							
FLUID CONDITION	Sodium	ppm	ASTM D5185m	0	3	6	
The BN result indicates that there is suitable alkalinity remaining in the	Boron	ppm	ASTM D5185m		22	112	
oil. The condition of the oil is suitable for further service.	Barium	ppm	ASTM D5185m		<1 67	0	
	Molybdenum Manganese	ppm	ASTM D5185m ASTM D5185m		67 <1	102 <1	
		ppm			914	643	
	Magnesium Calcium	ppm	ASTM D5185m ASTM D5185m		1088	1479	
	Phosphorus	ppm	ASTM D5185m		1011	791	
	Zinc	ppm	ASTM D5185m		1195	945	
	Sulfur	ppm	ASTM D5185m		3206	4109	
	Oxidation	Abs/.1mm	*ASTM D7414		14.1	14.1	
	Base Number (BN)		ASTM D2896		8.5	7.4	
	Dado Hambor (DIA)	mg nor rg	.101111 DE000	0.0	0.0	7.1	













Certificate L2367

Laboratory Sample No. Lab Number

Unique Number : 10836122

: GFL0108167 : 06064740 Test Package : FLEET

: WearCheck USA - 501 Madison Ave., Cary, NC 27513 Recieved : 18 Jan 2024 : 19 Jan 2024 Diagnosed

Diagnostician : Wes Davis

To discuss this sample report, contact Customer Service at 1-800-237-1369. \* - Denotes test methods that are outside of the ISO 17025 scope of accreditation. GFL Environmental - 975 - Houston East Hwy 3 - East 10200 Old Galveston Rd 974 Houston, TX US 77034

Contact: Jorge Tamez jtamez@gflenv.com T: (832)405-4630

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)