



VOLVO

OIL ANALYSIS REPORT

WEAR	NORMAL
CONTAMINATION	NORMAL
FLUID CONDITION	NORMAL



Area
[A11839]
Machine Id
VOLVO L120H 633139
Component
Diesel Engine
Fluid
MOBIL 15W40 (--- GAL)

RECOMMENDATION

Resample at the next service interval to monitor.

Test	UOM	Method	Limit/Abn	Current	History1	History2
Sample Number		Client Info		VCP428751	VCP430671	VCP421860
Sample Date		Client Info		05 Dec 2023	23 Oct 2023	22 Aug 2023
Machine Age	hrs	Client Info		4190	3630	3210
Oil Age	hrs	Client Info		250	250	250
Filter Age	hrs	Client Info		0	0	0
Oil Changed		Client Info		Changed	Changed	Changed
Filter Changed		Client Info		Changed	Changed	Changed
Sample Status				NORMAL	NORMAL	NORMAL

WEAR

All component wear rates are normal.

Iron	ppm	ASTM D5185m	>200	3	8	5
Chromium	ppm	ASTM D5185m	>20	0	<1	0
Nickel	ppm	ASTM D5185m	>5	0	0	0
Titanium	ppm	ASTM D5185m		<1	<1	<1
Silver	ppm	ASTM D5185m	>2	<1	<1	0
Aluminum	ppm	ASTM D5185m	>30	2	2	4
Lead	ppm	ASTM D5185m	>40	<1	0	0
Copper	ppm	ASTM D5185m	>20	<1	<1	<1
Tin	ppm	ASTM D5185m	>20	<1	<1	<1
Vanadium	ppm	ASTM D5185m		0	0	0
White Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE

CONTAMINATION











There is no indication of any contamination in the oil.

Silicon	ppm	ASTM D5185m	>20	3	4	4
Potassium	ppm	ASTM D5185m	>20	2	0	<1
Fuel		WC Method	>6.0	<1.0	<1.0	<1.0
Water		WC Method	>0.2	NEG	NEG	NEG
Glycol		WC Method		NEG	NEG	NEG
Soot %	%	*ASTM D7844	>3	0.1	0.2	0.2
Nitration	Abs/cm	*ASTM D7624	>20	6.0	6.6	6.1
Sulfation	Abs/.1mm	*ASTM D7415	>30	16.0	17.0	15.9
Silt	scalar	*Visual	NONE	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.2	NEG	NEG	NEG

FLUID CONDITION

The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

Sodium	ppm	ASTM D5185m	>118	<1	2	2
Boron	ppm	ASTM D5185m		7	11	12
Barium	ppm	ASTM D5185m		0	0	0
Molybdenum	ppm	ASTM D5185m		8	24	29
Manganese	ppm	ASTM D5185m		<1	<1	<1
Magnesium	ppm	ASTM D5185m		115	346	394
Calcium	ppm	ASTM D5185m		2076	1853	1972
Phosphorus	ppm	ASTM D5185m		932	821	996
Zinc	ppm	ASTM D5185m		1072	1146	1179
Sulfur	ppm	ASTM D5185m		3536	3504	4325
Oxidation	Abs/.1mm	*ASTM D7414	>25	9.1	10.7	10.2
Base Number (BN)	mg KOH/g	ASTM D2896		6.9	7.4	7.8
Visc @ 100°C	cSt	ASTM D445		13.3	13.1	13.6



Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513
Sample No. : VCP428751 **Received** : 18 Jan 2024
Lab Number : 06064954 **Diagnosed** : 19 Jan 2024
Unique Number : 10836336 **Diagnostician** : Wes Davis
Test Package : MOB 1 (Additional Tests: TBN)

GOURMETS DELIGHT
 PO BOX 160
 AVONDALE, PA
 US 19311
 Contact: GABE VALENTINO
 gabe.valentino@gourmetsfinest.com
 T: (610)268-3578
 F: (610)268-2298

Certificate L2367
 To discuss this sample report, contact Customer Service at 1-800-237-1369.
 * - Denotes test methods that are outside of the ISO 17025 scope of accreditation.
 Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)