



OIL ANALYSIS REPORT

WEAR	NORMAL
CONTAMINATION	NORMAL
FLUID CONDITION	NORMAL

Area
5509 CHAMPIONS DR
 Machine Id
MRC-292
 Component
Compressor
 Fluid
TULCO LUBSOIL LPG WS 150 (--- GAL)

RECOMMENDATION

Resample at the next service interval to monitor.

Test	UOM	Method	Limit/Abn	Current	History1	History2
Sample Number		Client Info		TO60001963	TO60001913	TO60001755
Sample Date		Client Info		10 Jan 2024	02 Dec 2023	05 Nov 2023
Machine Age	hrs	Client Info		8163	7436	6777
Oil Age	hrs	Client Info		0	0	0
Filter Age	hrs	Client Info		0	0	0
Oil Changed		Client Info		N/A	Not Changd	N/A
Filter Changed		Client Info		N/A	Not Changd	N/A
Sample Status				NORMAL	NORMAL	NORMAL

WEAR

All component wear rates are normal.

Iron	ppm	ASTM D5185m	>50	<1	<1	0
Chromium	ppm	ASTM D5185m	>10	<1	0	0
Nickel	ppm	ASTM D5185m		0	0	0
Titanium	ppm	ASTM D5185m		<1	0	0
Silver	ppm	ASTM D5185m		0	0	0
Aluminum	ppm	ASTM D5185m	>25	2	<1	<1
Lead	ppm	ASTM D5185m	>25	<1	<1	0
Copper	ppm	ASTM D5185m	>50	<1	<1	1
Tin	ppm	ASTM D5185m	>15	<1	0	0
Vanadium	ppm	ASTM D5185m		0	<1	<1
White Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE

CONTAMINATION











The amount and size of particulates present in the system are acceptable. There is no indication of any contamination in the oil.

Silicon	ppm	ASTM D5185m	>25	2	5	2
Potassium	ppm	ASTM D5185m	>20	3	0	1
Water	%	ASTM D6304	>2.26	0.006	0.011	0.016
ppm Water	ppm	ASTM D6304	>22600	64	117	165.9
Particles >4µm		ASTM D7647	>10000	3290	2661	4214
Particles >6µm		ASTM D7647	>1300	387	750	1209
Particles >14µm		ASTM D7647	>320	14	55	64
Particles >21µm		ASTM D7647	>80	4	11	11
Particles >38µm		ASTM D7647	>20	0	0	2
Particles >71µm		ASTM D7647	>4	0	0	2
Oil Cleanliness		ISO 4406 (c)	>20/17/15	19/16/11	19/17/13	19/17/13
Silt	scalar	*Visual	NONE	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	LIGHT	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>2.26	NEG	NEG	NEG

FLUID CONDITION

The AN level is acceptable for this fluid. The condition of the oil is suitable for further service.

Sodium	ppm	ASTM D5185m		0	3	2
Boron	ppm	ASTM D5185m	0	66	87	99
Barium	ppm	ASTM D5185m	0	<1	0	0
Molybdenum	ppm	ASTM D5185m	0	<1	<1	<1
Manganese	ppm	ASTM D5185m		0	0	<1
Magnesium	ppm	ASTM D5185m	0	6	8	8
Calcium	ppm	ASTM D5185m	0	1212	1322	1277
Phosphorus	ppm	ASTM D5185m	0	321	312	306
Zinc	ppm	ASTM D5185m	0	284	321	322
Sulfur	ppm	ASTM D5185m	0	3221	2689	1662
Acid Number (AN)	mg KOH/g	ASTM D8045		0.618	1.23	0.62
Visc @ 40°C	cSt	ASTM D445	151	131	131	131
Visc @ 100°C	cSt	ASTM D445	28	13.5	13.5	13.4
Viscosity Index (VI)	Scale	ASTM D2270	224	97	97	96



Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513
Sample No. : TO60001963 **Received** : 18 Jan 2024
Lab Number : 06065053 **Diagnosed** : 22 Jan 2024
Unique Number : 10836435 **Diagnostician** : Don Baldrige
Test Package : MOB 2 (Additional Tests: KF, KV100, PrtCount, VI)

MIDLAND - EOG RESOURCES INC.
 5509 CHAMPIONS DRIVE
 MIDLAND, TX
 US 79706
 Contact: HERMAN GARZA
 herman_garza@eogresources.com
 T: (432)686-3600
 F:

To discuss this sample report, contact Customer Service at 1-800-237-1369.

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)