



WEAR	NORMAL
CONTAMINATION	NORMAL
FLUID CONDITION	NORMAL

Machine Id
SIGNET MISCHIEF
Component
Port Main Engine
Fluid
CHEVRON DELO 400 LE 15W40 (70 GAL)

RECOMMENDATION

Resample at the next service interval to monitor. Please specify the component make and model with your next sample.

Test	UOM	Method	Limit/Abn	Current	History1	History2
Sample Number		Client Info		MW0059748	MW0059785	MW0045602
Sample Date		Client Info		10 Jan 2024	02 Oct 2023	05 Jul 2023
Machine Age	hrs	Client Info		18473	18150	17876
Oil Age	hrs	Client Info		1260	937	661
Filter Age	hrs	Client Info		260	437	161
Oil Changed		Client Info		Not Changd	Not Changd	Not Changd
Filter Changed		Client Info		Not Changd	Not Changd	N/A
Sample Status				NORMAL	NORMAL	NORMAL

WEAR

All component wear rates are normal.

Iron	ppm	ASTM D5185m	>75	5	2	3
Chromium	ppm	ASTM D5185m	>8	0	0	<1
Nickel	ppm	ASTM D5185m	>2	0	0	0
Titanium	ppm	ASTM D5185m	>3	8	9	10
Silver	ppm	ASTM D5185m	>2	0	0	0
Aluminum	ppm	ASTM D5185m	>15	2	<1	2
Lead	ppm	ASTM D5185m	>18	0	0	0
Copper	ppm	ASTM D5185m	>80	2	2	2
Tin	ppm	ASTM D5185m	>14	<1	0	0
Vanadium	ppm	ASTM D5185m		<1	<1	<1
White Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE

CONTAMINATION







There is no indication of any contamination in the oil.

Silicon	ppm	ASTM D5185m	>20	4	4	3
Potassium	ppm	ASTM D5185m	>20	2	0	3
Fuel		WC Method	>4.0	<1.0	<1.0	<1.0
Water		WC Method	>0.1	NEG	NEG	NEG
Glycol		WC Method		NEG	NEG	NEG
Soot %	%	*ASTM D7844		0.1	0.1	0.1
Nitration	Abs/cm	*ASTM D7624	>20	8.2	8.3	8.1
Sulfation	Abs/.1mm	*ASTM D7415	>30	20.4	19.9	19.3
Silt	scalar	*Visual	NONE	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.1	NEG	NEG	NEG

FLUID CONDITION

The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

Sodium	ppm	ASTM D5185m	>75	2	2	<1
Boron	ppm	ASTM D5185m		186	154	158
Barium	ppm	ASTM D5185m		<1	0	0
Molybdenum	ppm	ASTM D5185m		70	62	57
Manganese	ppm	ASTM D5185m		<1	<1	<1
Magnesium	ppm	ASTM D5185m		687	702	700
Calcium	ppm	ASTM D5185m		1527	1610	1684
Phosphorus	ppm	ASTM D5185m	1200	794	772	772
Zinc	ppm	ASTM D5185m	1300	893	910	922
Sulfur	ppm	ASTM D5185m	3200	2968	3071	3754
Oxidation	Abs/.1mm	*ASTM D7414	>25	15.2	15.1	14.6
Base Number (BN)	mg KOH/g	ASTM D2896	9.6	7.6	7.8	8.2
Visc @ 100°C	cSt	ASTM D445	15.7	13.0	13.2	13.3



Certificate L2367

Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513
Sample No. : MW0059748 **Received** : 19 Jan 2024
Lab Number : 06065338 **Diagnosed** : 24 Jan 2024
Unique Number : 10836720 **Diagnostician** : Wes Davis
Test Package : MAR 2

To discuss this sample report, contact Customer Service at 1-800-237-1369.

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

MARITIME COMPANY
 3802 PORT RIVER RD
 PASCAGOULA, MS
 US 39567

Contact: MARK KOPSYWA
 mark.kopszywa@signetmaritime.com

T:
 F: (228)769-0629