



WEAR	NORMAL
CONTAMINATION	NORMAL
FLUID CONDITION	NORMAL

Area
(ECU365)
Machine Id
2869
Component
Diesel Engine
Fluid
PETRO CANADA DURON SHP 15W40 (7 GAL)

RECOMMENDATION

Resample at the next service interval to monitor.

Test	UOM	Method	Limit/Abn	Current	History1	History2
Sample Number		Client Info		GFL0109877	GFL0107257	GFL0097931
Sample Date		Client Info		18 Jan 2024	29 Dec 2023	02 Nov 2023
Machine Age	hrs	Client Info		3003	2868	2607
Oil Age	hrs	Client Info		272	137	380
Filter Age	hrs	Client Info		272	137	380
Oil Changed		Client Info		Not Changd	Not Changd	Not Changd
Filter Changed		Client Info		Not Changd	Not Changd	Not Changd
Sample Status				NORMAL	NORMAL	NORMAL

WEAR

All component wear rates are normal.

Iron	ppm	ASTM D5185m	>165	13	5	17
Chromium	ppm	ASTM D5185m	>5	<1	<1	<1
Nickel	ppm	ASTM D5185m	>4	0	0	0
Titanium	ppm	ASTM D5185m	>2	0	0	<1
Silver	ppm	ASTM D5185m	>2	0	0	0
Aluminum	ppm	ASTM D5185m	>20	2	2	4
Lead	ppm	ASTM D5185m	>150	0	0	<1
Copper	ppm	ASTM D5185m	>90	1	3	2
Tin	ppm	ASTM D5185m	>5	0	<1	<1
Vanadium	ppm	ASTM D5185m		<1	0	<1
White Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE

CONTAMINATION







There is no indication of any contamination in the oil.

Silicon	ppm	ASTM D5185m	>35	6	3	7
Potassium	ppm	ASTM D5185m	>20	<1	<1	4
Fuel		WC Method	>3.0	<1.0	<1.0	<1.0
Water		WC Method	>0.2	NEG	NEG	NEG
Glycol		WC Method		NEG	NEG	NEG
Soot %	%	*ASTM D7844	>7.5	0.5	0.2	0.4
Nitration	Abs/cm	*ASTM D7624	>20	6.1	5.5	8.2
Sulfation	Abs/.1mm	*ASTM D7415	>30	17.6	16.8	19.2
Silt	scalar	*Visual	NONE	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.2	NEG	NEG	NEG

FLUID CONDITION

The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

Sodium	ppm	ASTM D5185m		5	0	<1
Boron	ppm	ASTM D5185m	0	8	8	8
Barium	ppm	ASTM D5185m	0	0	0	0
Molybdenum	ppm	ASTM D5185m	60	63	57	58
Manganese	ppm	ASTM D5185m	0	<1	<1	<1
Magnesium	ppm	ASTM D5185m	1010	932	831	823
Calcium	ppm	ASTM D5185m	1070	1085	979	1050
Phosphorus	ppm	ASTM D5185m	1150	1018	995	877
Zinc	ppm	ASTM D5185m	1270	1254	1129	1127
Sulfur	ppm	ASTM D5185m	2060	3170	2788	2686
Oxidation	Abs/.1mm	*ASTM D7414	>25	12.2	12.4	14.5
Base Number (BN)	mg KOH/g	ASTM D2896	9.8	8.3	7.8	7.8
Visc @ 100°C	cSt	ASTM D445	15.4	13.1	12.7	12.4



Certificate L2367

Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513
Sample No. : GFL0109877 **Received** : 19 Jan 2024
Lab Number : 06065411 **Diagnosed** : 22 Jan 2024
Unique Number : 10836793 **Diagnostician** : Wes Davis
Test Package : FLEET

GFL Environmental - 010 - Stockbridge
 1280 Rum Creek Parkway
 Stockbridge, GA
 US 30281
 Contact: JOSHUA TINKER
 joshuatinker@gflenv.com

To discuss this sample report, contact Customer Service at 1-800-237-1369.

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

T:
F: