



WEAR	NORMAL
CONTAMINATION	NORMAL
FLUID CONDITION	NORMAL



Machine Id
JOHN DEERE 650K 1T0650KKEHF318440
 Component
Diesel Engine
 Fluid
Diesel Engine Oil (--- GAL)

RECOMMENDATION

Resample at the next service interval to monitor.

Test	UOM	Method	Limit/Abn	Current	History1	History2
Sample Number		Client Info		JR0198850	JR0171162	JR0161662
Sample Date		Client Info		17 Jan 2024	16 Jun 2023	12 Apr 2023
Machine Age	hrs	Client Info		4992	4469	4173
Oil Age	hrs	Client Info		523	500	500
Filter Age	hrs	Client Info		0	500	500
Oil Changed		Client Info		Changed	Changed	Changed
Filter Changed		Client Info		Changed	Changed	Changed
Sample Status				NORMAL	NORMAL	ABNORMAL

WEAR

All component wear rates are normal.

Iron	ppm	ASTM D5185m	>51	23	19	▲ 61
Chromium	ppm	ASTM D5185m	>11	<1	<1	1
Nickel	ppm	ASTM D5185m	>5	<1	<1	<1
Titanium	ppm	ASTM D5185m		0	0	<1
Silver	ppm	ASTM D5185m	>3	0	0	0
Aluminum	ppm	ASTM D5185m	>31	5	4	6
Lead	ppm	ASTM D5185m	>26	12	8	▲ 56
Copper	ppm	ASTM D5185m	>26	2	1	4
Tin	ppm	ASTM D5185m	>4	<1	<1	1
Vanadium	ppm	ASTM D5185m		<1	0	0
White Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE

CONTAMINATION







There is no indication of any contamination in the oil.

Silicon	ppm	ASTM D5185m	>22	9	8	10
Potassium	ppm	ASTM D5185m	>20	<1	2	2
Fuel		WC Method	>2.1	<1.0	<1.0	<1.0
Water		WC Method	>0.21	NEG	NEG	NEG
Glycol		WC Method		NEG	NEG	NEG
Soot %	%	*ASTM D7844	>3	0.8	0.6	1.2
Nitration	Abs/cm	*ASTM D7624	>20	9.7	9.7	12.1
Sulfation	Abs/.1mm	*ASTM D7415	>30	24.6	23.6	27.3
Silt	scalar	*Visual	NONE	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.21	NEG	NEG	NEG

FLUID CONDITION

The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

Sodium	ppm	ASTM D5185m	>31	2	2	<1
Boron	ppm	ASTM D5185m		125	213	61
Barium	ppm	ASTM D5185m		<1	3	3
Molybdenum	ppm	ASTM D5185m		251	245	269
Manganese	ppm	ASTM D5185m		<1	<1	1
Magnesium	ppm	ASTM D5185m		855	764	795
Calcium	ppm	ASTM D5185m		1579	1401	1455
Phosphorus	ppm	ASTM D5185m		962	886	851
Zinc	ppm	ASTM D5185m		1189	1088	1079
Sulfur	ppm	ASTM D5185m		3246	3345	2968
Oxidation	Abs/.1mm	*ASTM D7414	>25	18.6	18.0	23.5
Base Number (BN)	mg KOH/g	ASTM D2896		7.4	8.8	6.3
Visc @ 100°C	cSt	ASTM D445		13.7	14.3	14.4



Certificate L2367

Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513
Sample No. : JR0198850 **Received** : 19 Jan 2024
Lab Number : 06065431 **Diagnosed** : 22 Jan 2024
Unique Number : 10836813 **Diagnostician** : Don Baldrige
Test Package : CONST (Additional Tests: TBN)

To discuss this sample report, contact Customer Service at 1-800-237-1369.

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

JRE - CHARLOTTE
 9550 STATESVILLE ROAD
 CHARLOTTE, NC
 US 28269
 Contact: CHARLOTTE SHOP
 myoung@jamesriverequipment.com
 T: (704)597-0211
 F: (704)596-6198