



WEAR	NORMAL
CONTAMINATION	NORMAL
FLUID CONDITION	NORMAL



Machine Id
JOHN DEERE 544K 1DW544KZVHF683402

Component
Hydraulic System

Fluid
JOHN DEERE HYDRAU (--- GAL)

RECOMMENDATION

Resample at the next service interval to monitor.

Test	UOM	Method	Limit/Abn	Current	History1	History2
Sample Number		Client Info		JR0199798	JR0148069	JR0124471
Sample Date		Client Info		18 Jan 2024	19 Jan 2023	08 Apr 2022
Machine Age	hrs	Client Info		4441	3962	3472
Oil Age	hrs	Client Info		0	3962	3472
Filter Age	hrs	Client Info		0	3962	3472
Oil Changed		Client Info		Not Chngd	Changed	Not Chngd
Filter Changed		Client Info		Not Chngd	Changed	Not Chngd
Sample Status				NORMAL	NORMAL	NORMAL

WEAR

All component wear rates are normal.

PQ		ASTM D8184	>50	14	12	17
Iron	ppm	ASTM D5185m	>71	4	19	17
Chromium	ppm	ASTM D5185m	>11	7	13	12
Nickel	ppm	ASTM D5185m	>6	0	0	0
Titanium	ppm	ASTM D5185m		0	0	0
Silver	ppm	ASTM D5185m		<1	<1	<1
Aluminum	ppm	ASTM D5185m	>11	0	1	1
Lead	ppm	ASTM D5185m	>13	0	1	1
Copper	ppm	ASTM D5185m	>21	2	2	2
Tin	ppm	ASTM D5185m	>5	0	<1	<1
Vanadium	ppm	ASTM D5185m		0	<1	0
White Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE

CONTAMINATION










The system cleanliness is acceptable for your target ISO 4406 cleanliness code. The system and fluid cleanliness is acceptable.

Silicon	ppm	ASTM D5185m	>24	1	3	3
Potassium	ppm	ASTM D5185m	>20	0	2	2
Water		WC Method	>0.075	NEG	NEG	NEG
Particles >4µm		ASTM D7647	>80000	3371	8604	11300
Particles >6µm		ASTM D7647	>5000	1146	1208	129
Particles >14µm		ASTM D7647	>640	126	156	12
Particles >21µm		ASTM D7647	>160	39	39	5
Particles >38µm		ASTM D7647	>40	2	2	0
Particles >71µm		ASTM D7647	>10	0	0	0
Oil Cleanliness		ISO 4406 (c)	>23/19/16	19/17/14	20/17/14	21/14/11
Silt	scalar	*Visual	NONE	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.075	NEG	NEG	NEG

FLUID CONDITION

The AN level is acceptable for this fluid. The condition of the oil is suitable for further service.

Sodium	ppm	ASTM D5185m	>21	2	3	4
Boron	ppm	ASTM D5185m		0	2	5
Barium	ppm	ASTM D5185m		0	1	0
Molybdenum	ppm	ASTM D5185m		0	2	3
Manganese	ppm	ASTM D5185m		<1	<1	<1
Magnesium	ppm	ASTM D5185m		5	9	11
Calcium	ppm	ASTM D5185m	87	140	213	247
Phosphorus	ppm	ASTM D5185m	727	626	630	623
Zinc	ppm	ASTM D5185m	900	788	862	826
Sulfur	ppm	ASTM D5185m	1500	1514	1720	1486
Acid Number (AN)	mg KOH/g	ASTM D8045	1.0	0.53	0.59	0.70
Visc @ 40°C	cSt	ASTM D445	65	60.4	59.3	58.9



Certificate L2367

Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513
Sample No. : JR0199798 **Received** : 19 Jan 2024
Lab Number : 06065514 **Diagnosed** : 23 Jan 2024
Unique Number : 10836896 **Diagnostician** : Wes Davis
Test Package : CONST (Additional Tests: PQ)

To discuss this sample report, contact Customer Service at 1-800-237-1369.

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

JRE - ASHLAND
 11047 LEADBETTER RD
 ASHLAND, VA
 US 23005
 Contact: DAVID ZIEG
 dzieg@jamesriverequipment.com
 T: (804)798-6001
 F: (804)798-0292